

Series # 502

Material group	Hardness		SFM	Feed Rate - IPR									
	HRC	BHN		1/16 in. 1.590 mm	1/8 in. 3.170 mm	1/4 in. 6.350 mm	3/8 in. 9.520 mm	1/2 in. 12.700 mm	5/8 in. 15.870 mm	3/4 in. 19.050 mm	1 in. 25.400 mm	1 1/4 in. 31.750 mm	1 1/2 in. 38.100 mm
Common structural steels	-	≤ 150	70	0.0015	0.0040	0.0065	0.0080	0.0100					
	≤ 32	≤ 301	55	0.0012	0.0030	0.0050	0.0065	0.0080					
Free-cutting steels	≤ 25	≤ 255	70	0.0015	0.0040	0.0065	0.0080	0.0100					
	≤ 32	≤ 301	55	0.0012	0.0030	0.0050	0.0065	0.0080					
Unalloyed heat-treatable steels	≤ 20	≤ 220	70	0.0012	0.0030	0.0050	0.0065	0.0080					
	≤ 25	≤ 255	55	0.0012	0.0030	0.0050	0.0065	0.0080					
	≤ 32	≤ 301											
Alloyed heat-treatable steels	≤ 32	≤ 301	35	0.0010	0.0025	0.0040	0.0050	0.0065					
	≤ 43	≤ 402											
Unalloyed case hardened steels	≤ 25	≤ 255	70	0.0015	0.0040	0.0065	0.0080	0.0100					
Alloyed case hardened steels	≤ 32	≤ 301	30	0.0010	0.0025	0.0040	0.0050	0.0065					
	≤ 43	≤ 402											
Nitriding steels	≤ 32	≤ 301	25	0.0010	0.0025	0.0040	0.0050	0.0065					
	≤ 43	≤ 402											
Tool steels	≤ 25	≤ 255	35	0.0010	0.0025	0.0040	0.0050	0.0065					
	≤ 43	≤ 402	15	0.0007	0.0020	0.0030	0.0040	0.0050					
High speed steels	≤ 43	≤ 402	15	0.0007	0.0020	0.0030	0.0040	0.0050					
Spring steels	≤ 38	≤ 354											
Hardened steels	≤ 48	≤ 460											
	≤ 66	-											
Stainless steels, sulphured austenitic martensitic	≤ 28	≤ 273	25	0.0010	0.0025	0.0040	0.0050	0.0065					
	≤ 36	≤ 337											
	≤ 46	≤ 435											
Cast iron	≤ 23	≤ 242	70	0.0015	0.0040	0.0065	0.0080	0.0100					
	≤ 38	≤ 354	55	0.0015	0.0040	0.0065	0.0080	0.0100					
Spheroidal graphite iron and malleable cast iron	≤ 23	≤ 242	65	0.0015	0.0040	0.0065	0.0080	0.0100					
	≤ 38	≤ 354	45	0.0015	0.0040	0.0065	0.0080	0.0100					
Chilled cast iron	≤ 38	≤ 354											
New cast materials GGV	≤ 20	≤ 220											
	≤ 32	≤ 301											
New cast materials ADI	≤ 32	≤ 301											
	≤ 43	≤ 402											
Special alloys	≤ 54	≤ 549											
Ti and Ti-alloys	≤ 25	≤ 255											
	≤ 43	≤ 402											
Aluminium and Al-alloys	-	≤ 120											
Al wrought alloys	-	≤ 200											
Al cast alloys ≤ 10 % Si ≤ 24 % Si	-	≤ 180	145	0.0017	0.0050	0.0080	0.0100	0.0125					
	-	≤ 180	115	0.0015	0.0040	0.0065	0.0080	0.0100					
Magnesium alloys	-	≤ 120	180	0.0015	0.0040	0.0065	0.0080	0.0100					
Copper, low-alloyed	-	≤ 150	70	0.0012	0.0030	0.0050	0.0065	0.0080					
Brass, short-chipping long-chipping	-	≤ 180											
	-	≤ 180	90	0.0012	0.0030	0.0050	0.0065	0.0080					
Bronze, short-chipping	-	≤ 180	70	0.0010	0.0025	0.0040	0.0050	0.0065					
	≤ 25	≤ 255	65	0.0010	0.0025	0.0040	0.0050	0.0065					
Bronze, long-chipping	≤ 25	≤ 255	55	0.0010	0.0025	0.0040	0.0050	0.0065					
	≤ 32	≤ 301											
Duroplastics Thermoplastics Reinforced plastics - Kevlar Reinforced plastics - GFK / CFK			35 55	0.0010 0.0012	0.0025 0.0030	0.0040 0.0050	0.0050 0.0065	0.0065 0.0080					

Series # 503

Material group	Hardness		SFM	Feed Rate - IPR									
	HRC	BHN		1/16 in. 1.590 mm	1/8 in. 3.170 mm	1/4 in. 6.350 mm	3/8 in. 9.520 mm	1/2 in. 12.700 mm	5/8 in. 15.870 mm	3/4 in. 19.050 mm	1 in. 25.400 mm	1 1/4 in. 31.750 mm	1 1/2 in. 38.100 mm
Common structural steels	-	≤ 150	70	0.0015	0.0040	0.0065	0.0080	0.0100	0.0100				
	≤ 32	≤ 301	55	0.0012	0.0030	0.0050	0.0065	0.0080	0.0080				
Free-cutting steels	≤ 25	≤ 255	70	0.0015	0.0040	0.0065	0.0080	0.0100	0.0100				
	≤ 32	≤ 301	55	0.0012	0.0030	0.0050	0.0065	0.0080	0.0080				
Unalloyed heat-treatable steels	≤ 20	≤ 220	70	0.0012	0.0030	0.0050	0.0065	0.0080	0.0080				
	≤ 25	≤ 255	55	0.0012	0.0030	0.0050	0.0065	0.0080	0.0080				
	≤ 32	≤ 301											
Alloyed heat-treatable steels	≤ 32	≤ 301	35	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065				
	≤ 43	≤ 402											
Unalloyed case hardened steels	≤ 25	≤ 255	70	0.0015	0.0040	0.0065	0.0080	0.0100	0.0100				
Alloyed case hardened steels	≤ 32	≤ 301	30	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065				
	≤ 43	≤ 402											
Nitriding steels	≤ 32	≤ 301	25	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065				
	≤ 43	≤ 402											
Tool steels	≤ 25	≤ 255	35	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065				
	≤ 43	≤ 402	15	0.0007	0.0020	0.0030	0.0040	0.0050	0.0050				
High speed steels	≤ 43	≤ 402	15	0.0007	0.0020	0.0030	0.0040	0.0050	0.0050				
Spring steels	≤ 38	≤ 354											
Hardened steels	≤ 48	≤ 460											
	≤ 66	-											
Stainless steels, sulphured austenitic martensitic	≤ 28	≤ 273	25	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065				
	≤ 36	≤ 337											
	≤ 46	≤ 435											
Cast iron	≤ 23	≤ 242	70	0.0015	0.0040	0.0065	0.0080	0.0100	0.0100				
	≤ 38	≤ 354	55	0.0015	0.0040	0.0065	0.0080	0.0100	0.0100				
Spheroidal graphite iron and malleable cast iron	≤ 23	≤ 242	65	0.0015	0.0040	0.0065	0.0080	0.0100	0.0100				
	≤ 38	≤ 354	45	0.0015	0.0040	0.0065	0.0080	0.0100	0.0100				
Chilled cast iron	≤ 38	≤ 354											
New cast materials GGV	≤ 20	≤ 220											
	≤ 32	≤ 301											
New cast materials ADI	≤ 32	≤ 301											
	≤ 43	≤ 402											
Special alloys	≤ 54	≤ 549											
Ti and Ti-alloys	≤ 25	≤ 255											
	≤ 43	≤ 402											
Aluminium and Al-alloys	-	≤ 120											
Al wrought alloys	-	≤ 200											
Al cast alloys ≤ 10 % Si ≤ 24 % Si	-	≤ 180	145	0.0017	0.0050	0.0080	0.0100	0.0125	0.0125				
	-	≤ 180	115	0.0015	0.0040	0.0065	0.0080	0.0100	0.0100				
Magnesium alloys	-	≤ 120	180	0.0015	0.0040	0.0065	0.0080	0.0100	0.0100				
Copper, low-alloyed	-	≤ 150	70	0.0012	0.0030	0.0050	0.0065	0.0080	0.0080				
Brass, short-chipping long-chipping	-	≤ 180											
	-	≤ 180	90	0.0012	0.0030	0.0050	0.0065	0.0080	0.0080				
Bronze, short-chipping	-	≤ 180	70	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065				
	≤ 25	≤ 255	65	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065				
Bronze, long-chipping	≤ 25	≤ 255	55	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065				
	≤ 32	≤ 301											
Duroplastics Thermoplastics Reinforced plastics - Kevlar Reinforced plastics - GFK / CFK			35 55	0.0010 0.0012	0.0025 0.0030	0.0040 0.0050	0.0050 0.0065	0.0065 0.0080	0.0065 0.0080				