

Material group	Hardness		SFM	Feed Rate - IPR									
	HRC	BHN		1/16 in. 1.590 mm	1/8 in. 3.170 mm	1/4 in. 6.350 mm	3/8 in. 9.520 mm	1/2 in. 12.700 mm	5/8 in. 15.870 mm	3/4 in. 19.050 mm	1 in. 25.400 mm	1 1/4 in. 31.750 mm	1 1/2 in. 38.100 mm
Common structural steels	-	≤ 150	105		0.0039	0.0063	0.0098	0.0098	0.0098	0.0124	0.0157	0.0197	
	≤ 32	≤ 301	85		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157	0.0197	
Free-cutting steels	≤ 25	≤ 255	115		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
	≤ 32	≤ 301	110		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
Unalloyed heat-treatable steels	≤ 20	≤ 220	90		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
	≤ 25	≤ 255	90		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
Alloyed heat-treatable steels	≤ 32	≤ 301	70		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
	≤ 43	≤ 402	55		0.0020	0.0031	0.0049	0.0049	0.0063	0.0079	0.0098		
Unalloyed case hardened steels	≤ 25	≤ 255	110		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
Alloyed case hardened steels	≤ 32	≤ 301	65		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
	≤ 43	≤ 402	40		0.0020	0.0031	0.0049	0.0049	0.0063	0.0079	0.0098		
Nitriding steels	≤ 32	≤ 301	45		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
	≤ 43	≤ 402											
Tool steels	≤ 25	≤ 255	60		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
	≤ 43	≤ 402											
High speed steels	≤ 43	≤ 402											
Spring steels	≤ 38	≤ 354											
Hardened steels	≤ 48	≤ 460											
	≤ 66	-											
Stainless steels, sulphured austenitic martensitic	≤ 28	≤ 273	40		0.0020	0.0031	0.0049	0.0049	0.0063	0.0079	0.0098		
	≤ 36	≤ 337	25		0.0020	0.0031	0.0049	0.0049	0.0063	0.0079	0.0098		
	≤ 46	≤ 435	35		0.0020	0.0031	0.0049	0.0049	0.0063	0.0079	0.0098		
Cast iron	≤ 23	≤ 242	110		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
	≤ 38	≤ 354	110		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
Spheroidal graphite iron and malleable cast iron	≤ 23	≤ 242	90		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
	≤ 38	≤ 354	70		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
Chilled cast iron	≤ 38	≤ 354											
New cast materials GGV	≤ 20	≤ 220											
	≤ 32	≤ 301											
New cast materials ADI	≤ 32	≤ 301											
	≤ 43	≤ 402											
Special alloys	≤ 54	≤ 549											
Ti and Ti-alloys	≤ 25	≤ 255											
	≤ 43	≤ 402											
Aluminium and Al-alloys	-	≤ 120											
Al wrought alloys	-	≤ 200											
Al cast alloys ≤ 10 % Si ≤ 24 % Si	-	≤ 180											
	-	≤ 180	195		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
Magnesium alloys	-	≤ 120	260		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
Copper, low-alloyed	-	≤ 150	215		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
Brass, short-chipping long-chipping	-	≤ 180	230		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
	-	≤ 180	150		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
Bronze, short-chipping	-	≤ 180	110		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
	≤ 25	≤ 255	90		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
Bronze, long-chipping	≤ 25	≤ 255	50		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
	≤ 32	≤ 301	50		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
Duroplastics			70		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
Thermoplastics			120		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
Reinforced plastics - Kevlar													
Reinforced plastics - GFK / CFK													

Material group	Hardness		SFM	Feed Rate - IPR									
	HRC	BHN		1/16 in. 1.590 mm	1/8 in. 3.170 mm	1/4 in. 6.350 mm	3/8 in. 9.520 mm	1/2 in. 12.700 mm	5/8 in. 15.870 mm	3/4 in. 19.050 mm	1 in. 25.400 mm	1 1/4 in. 31.750 mm	1 1/2 in. 38.100 mm
Common structural steels	-	≤ 150	105		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
	≤ 32	≤ 301	85		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
Free-cutting steels	≤ 25	≤ 255	115		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
	≤ 32	≤ 301	110		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
Unalloyed heat-treatable steels	≤ 20	≤ 220	90		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
	≤ 25	≤ 255	90		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
Alloyed heat-treatable steels	≤ 32	≤ 301	70		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
	≤ 43	≤ 402	55		0.0020	0.0031	0.0049	0.0049	0.0063	0.0079	0.0098		
Unalloyed case hardened steels	≤ 25	≤ 255	110		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
Alloyed case hardened steels	≤ 32	≤ 301	65		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
	≤ 43	≤ 402	40		0.0020	0.0031	0.0049	0.0049	0.0063	0.0079	0.0098		
Nitriding steels	≤ 32	≤ 301	45		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
	≤ 43	≤ 402											
Tool steels	≤ 25	≤ 255	60		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
	≤ 43	≤ 402											
High speed steels	≤ 43	≤ 402											
Spring steels	≤ 38	≤ 354											
Hardened steels	≤ 48	≤ 460											
	≤ 66	-											
Stainless steels, sulphured austenitic martensitic	≤ 28	≤ 273	40		0.0020	0.0031	0.0049	0.0049	0.0063	0.0079	0.0098		
	≤ 36	≤ 337	25		0.0020	0.0031	0.0049	0.0049	0.0063	0.0079	0.0098		
	≤ 46	≤ 435	35		0.0020	0.0031	0.0049	0.0049	0.0063	0.0079	0.0098		
Cast iron	≤ 23	≤ 242	110		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
	≤ 38	≤ 354	110		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
Spheroidal graphite iron and malleable cast iron	≤ 23	≤ 242	90		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
	≤ 38	≤ 354	70		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
Chilled cast iron	≤ 38	≤ 354											
New cast materials GGV	≤ 20	≤ 220											
	≤ 32	≤ 301											
New cast materials ADI	≤ 32	≤ 301											
	≤ 43	≤ 402											
Special alloys	≤ 54	≤ 549											
Ti and Ti-alloys	≤ 25	≤ 255											
	≤ 43	≤ 402											
Aluminium and Al-alloys	-	≤ 120											
Al wrought alloys	-	≤ 200											
Al cast alloys ≤ 10 % Si ≤ 24 % Si	-	≤ 180											
	-	≤ 180	195		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
Magnesium alloys	-	≤ 120	260		0.0039	0.0063	0.0098	0.0098	0.0124	0.0157	0.0197		
Copper, low-alloyed	-	≤ 150	215		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
Brass, short-chipping long-chipping	-	≤ 180	230		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
	-	≤ 180	150		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
Bronze, short-chipping	-	≤ 180	110		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
	≤ 25	≤ 255	90		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
Bronze, long-chipping	≤ 25	≤ 255	50		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
	≤ 32	≤ 301	50		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
Duroplastics			70		0.0025	0.0039	0.0063	0.0063	0.0079	0.0098	0.0124		
Thermoplastics			120		0.0031	0.0049	0.0079	0.0079	0.0098	0.0124	0.0157		
Reinforced plastics - Kevlar													