











TuffCut® AL / X-AL

136 / 138 / 138N / 138R / 138NR Recommended Cutting Data - Profile Milling Inch

Workpiece Material Group	I S O	Coolant ● Preferred	Profile Milling (ae)				End Mill Diameter								
							1/8"	3/16"	1/4"	5/16"	3/8"	1/2"	5/8"	3/4"	1"
			10%	20%	30%	50%	ae > .3D use <1D ap ae < .2D use <2D ap *Profile Milling at > 25% ap is not recommended for diameters 1/4" and below.								
			3.8	3.1	2	1	← Multiply fz by this Factor based on ae. When finishing, use the standard fz per chart below. Only add chip thinning when roughing or semi-finishing.								
		Max.	vc - SFM				fz - in/tooth								
Non-Ferrous - Aluminum / Aluminum Alloys < 10% Si	N	•	2000	1800	1200	900	.0025	.0037	.0050	.0062	.0075	.0100	.0125	.0150	.0200
Non-Ferrous - Aluminum / Aluminum Alloys > 10% Si	N	•	1500	1200	1000	800	.0025	.0037	.0050	.0062	.0075	.0100	.0125	.0150	.0200
Non-Ferrous - Brass	N	•	900	800	600	500	.0025	.0037	.0050	.0062	.0075	.0100	.0125	.0150	.0200
Non-Ferrous - Cu/Cu Alloys / Magnesium	N	•	1000	800	600	500	.0025	.0037	.0050	.0062	.0075	.0100	.0125	.0150	.0200
Non-Ferrous - Plastics	N	•	900	800	600	500	.0025	.0037	.0050	.0062	.0075	.0100	.0125	.0150	.0200

Above 20,000 RPM, Tool Balancing Required

136 / 138 / 138N / 138R / 138NR Recommended Cutting Data - Profile Milling Metric

Workpiece Material Group	I S O	Coolant ● Preferred	Profile Milling (ae)				End Mill Diameter (mm)						
							3*	5*	6*	8	10	14	16
			10%	20%	30%	50%	ae > .3D use <1D ap ae < .2D use <2D ap *Profile Milling at > 25% ap is not recommended for diameters 6mm and below.						
			3.8	3.1	2	1	← Multiply fz by this Factor based on ae. When finishing, use the standard fz per chart below. Only add chip thinning when roughing or semi-finishing.						
		Max.	vc - m/min				fz - mm/tooth						
Non-Ferrous - Aluminum / Aluminum Alloys < 10% Si	N	•	600	550	365	275	.0600	.1000	.1200	.1600	.2000	.2800	.3200
Non-Ferrous - Aluminum / Aluminum Alloys > 10% Si	N	•	450	365	305	250	.0600	.1000	.1200	.1600	.2000	.2800	.3200
Non-Ferrous - Brass	N	•	275	250	180	150	.0600	.1000	.1200	.1600	.2000	.2800	.3200
Non-Ferrous - Cu/Cu Alloys / Magnesium	N	•	300	250	180	150	.0600	.1000	.1200	.1600	.2000	.2800	.3200
Non-Ferrous - Plastics	N	•	275	250	180	150	.0600	.1000	.1200	.1600	.2000	.2800	.3200

Above 20,000 RPM, Tool Balancing Required

Spindle Maximum - Should the calculated spindle speed be more than your actual spindle maximum, use this formula:
 (Calculated Feed x Spindle Maximum)/Calculated Speed

Technical data provided should be considered advisory only as variations may be necessary depending on the particular application.