

Taper Shank Drills

**Regular Shank / Core Drills
Silver and Deming Drills**

**List No. 601
List No. 575**

Workpiece Material		Carbon Steels		Alloy Steels		Die Steels Hardened Steels Stainless Steels		Cast Irons		Aluminum Alloys Nonferrous Metals	
Speed (SFM)		55 - 65 SFM		50 - 60 SFM		35 - 45 SFM		65 - 80 SFM		100 - 110 SFM	
Drill Diameter		55 - 65 SFM		50 - 60 SFM		35 - 45 SFM		65 - 80 SFM		100 - 110 SFM	
Fractional	Decimal	RPM	Feed (IPR)	RPM	Feed (IPR)	RPM	Feed (IPR)	RPM	Feed (IPR)	RPM	Feed (IPR)
1/8	0.1250	2,000	0.003	1,900	0.003	1,400	0.002	2,500	0.004	3,400	0.003
3/16	0.1875	1,400	0.004	1,300	0.004	920	0.003	1,700	0.005	2,300	0.005
1/4	0.2500	1,000	0.004	920	0.005	690	0.004	1,300	0.007	1,700	0.006
5/16	0.3125	800	0.004	740	0.005	560	0.005	980	0.008	1,400	0.008
3/8	0.3750	670	0.007	620	0.006	460	0.005	820	0.008	1,200	0.008
7/16	0.4375	570	0.007	530	0.006	400	0.005	700	0.009	970	0.009
1/2	0.5000	500	0.008	460	0.006	350	0.006	620	0.010	850	0.009
5/8	0.6250	400	0.009	370	0.008	280	0.007	490	0.012	680	0.012
3/4	0.7500	340	0.010	310	0.009	230	0.008	410	0.013	570	0.013
7/8	0.8750	290	0.011	270	0.009	200	0.008	350	0.014	490	0.014
1	1.0000	250	0.012	230	0.010	180	0.009	310	0.015	430	0.014
1 1/8	1.1250	230	0.012	210	0.011	160	0.010	280	0.016	380	0.015
1 1/4	1.2500	200	0.014	190	0.011	140	0.010	250	0.016	340	0.016
1 3/8	1.3750	190	0.014	170	0.012	130	0.010	230	0.017	310	0.017
1 1/2	1.5000	170	0.014	160	0.012	120	0.011	210	0.017	290	0.017
1 5/8	1.6250	160	0.015	150	0.013	110	0.011	190	0.017	260	0.017
1 3/4	1.7500	150	0.016	140	0.013	100	0.011	180	0.018	250	0.018
1 7/8	1.8750	140	0.016	130	0.014	100	0.012	170	0.019	230	0.019
2	2.0000	130	0.016	120	0.014	90	0.012	160	0.020	220	0.020

Taper Shank Oil Hole Drills / Cobalt

List No. 683

Workpiece Material		Carbon Steels		Alloy Steels Hardened Steels		Mold Steels Stainless Steels		Cast Irons		Aluminum Alloys Nonferrous Metals	
Speed (SFM)		55 - 65 SFM		50 - 60 SFM		35 - 45 SFM		65 - 80 SFM		100 - 110 SFM	
Drill Diameter		55 - 65 SFM		50 - 60 SFM		35 - 45 SFM		65 - 80 SFM		100 - 110 SFM	
Fractional	Decimal	RPM	Feed (IPR)	RPM	Feed (IPR)	RPM	Feed (IPR)	RPM	Feed (IPR)	RPM	Feed (IPR)
3/8	0.3750	680	0.008	620	0.007	460	0.006	820	0.010	1,200	0.010
7/16	0.4375	580	0.009	530	0.007	400	0.006	700	0.011	970	0.011
1/2	0.5000	510	0.009	460	0.008	350	0.007	620	0.012	850	0.012
5/8	0.6250	410	0.011	370	0.010	280	0.008	490	0.014	680	0.014
23/32	0.7188	360	0.012	320	0.010	240	0.009	430	0.015	590	0.014
3/4	0.7500	340	0.013	310	0.011	230	0.009	410	0.015	570	0.015
7/8	0.8750	290	0.013	270	0.011	200	0.010	350	0.017	490	0.017
1	1.0000	260	0.014	230	0.012	180	0.011	310	0.018	430	0.018
1 1/4	1.2500	210	0.016	190	0.013	140	0.011	250	0.019	340	0.019
1 1/2	1.5000	170	0.017	160	0.014	120	0.012	210	0.021	290	0.021

1) The above values apply when coolant is used in a vertical machine. In a horizontal machine or deep hole, use pecking.
2) Adjust drilling condition when unusual vibration or different sound occurs.