

■ Series 423002 323002 423001 323001 • NINA

Material Group	Side Milling (A) and Slotting (B)			K30F-TiCN			K30F-DCF			Recommended feed per tooth (fz = mm/th) for side milling (A). For slotting (B), reduce fz by 20%.									
	A		B	Cutting Speed – vc m/min			Cutting Speed – vc m/min			D1 – Diameter									
	ap	ae	ap	min	–	max	min	–	max	mm	2,0	3,0	4,0	5,0	6,0	8,0	10,0	12,0	
	ap	ae	ap	min	–	max	min	–	max	mm	2,0	3,0	4,0	5,0	6,0	8,0	10,0	12,0	
P	0	0,75 x D	0,5 x D	0,5 x D	150	–	200	150	–	200	fz	0,014	0,021	0,028	0,036	0,044	0,060	0,072	0,083
	1	0,75 x D	0,5 x D	0,5 x D	150	–	200	150	–	200	fz	0,014	0,021	0,028	0,036	0,044	0,060	0,072	0,083
	2	0,75 x D	0,5 x D	0,5 x D	140	–	190	140	–	190	fz	0,014	0,021	0,028	0,036	0,044	0,060	0,072	0,083
	3	0,75 x D	0,5 x D	0,5 x D	120	–	160	120	–	160	fz	0,011	0,017	0,023	0,030	0,036	0,050	0,061	0,070
	4	0,75 x D	0,5 x D	0,5 x D	90	–	150	90	–	150	fz	0,010	0,016	0,021	0,027	0,033	0,045	0,054	0,062
M	1	0,75 x D	0,5 x D	0,5 x D	90	–	115	90	–	115	fz	0,011	0,017	0,023	0,030	0,036	0,050	0,061	0,070
	2	0,75 x D	0,5 x D	0,5 x D	60	–	80	60	–	80	fz	0,009	0,014	0,019	0,024	0,029	0,040	0,048	0,056
K	1	0,75 x D	0,5 x D	0,5 x D	120	–	150	120	–	150	fz	0,014	0,021	0,028	0,036	0,044	0,060	0,072	0,083
	2	0,75 x D	0,5 x D	0,5 x D	110	–	140	110	–	140	fz	0,011	0,017	0,023	0,030	0,036	0,050	0,061	0,070
N	1	0,75 x D	0,5 x D	0,5 x D	500	–	2000	500	–	2000	fz	0,020	0,030	0,040	0,050	0,060	0,080	0,100	0,120
	2	0,75 x D	0,5 x D	0,5 x D	500	–	1500	500	–	1500	fz	0,018	0,027	0,036	0,045	0,054	0,072	0,090	0,108
	5	0,75 x D	0,5 x D	0,5 x D	250	–	1000	250	–	1000	fz	0,018	0,027	0,036	0,045	0,054	0,072	0,090	0,108

NOTE: Lower value of cutting speed is used for high stock removal applications or for higher hardness (machinability) within group.
Higher value of cutting speed is used for finishing applications or for lower hardness (machinability) within group.

Application Data • Series 423004 423003 • NINA

■ Series 423004 423003 • NINA

Material Group	Side Milling (A) and Slotting (B)			K30F-DCHP			Recommended feed per tooth (fz = mm/th) for side milling (A). For slotting (B), reduce fz by 20%.							
	A		B	Cutting Speed – vc m/min			D1 – Diameter							
	ap	ae	ap	min	–	max	mm	4,0	5,0	6,0	8,0	10,0	12,0	
	ap	ae	ap	min	–	max	mm	4,0	5,0	6,0	8,0	10,0	12,0	
P	0	1 x D	0,5 x D	1 x D	150	–	200	fz	0,028	0,036	0,044	0,060	0,072	0,083
	1	1 x D	0,5 x D	1 x D	150	–	200	fz	0,028	0,036	0,044	0,060	0,072	0,083
	2	1 x D	0,5 x D	1 x D	140	–	190	fz	0,028	0,036	0,044	0,060	0,072	0,083
	3	1 x D	0,5 x D	1 x D	120	–	160	fz	0,023	0,030	0,036	0,050	0,061	0,070
	4	1 x D	0,5 x D	1 x D	90	–	150	fz	0,021	0,027	0,033	0,045	0,054	0,062
M	1	1 x D	0,5 x D	1 x D	90	–	115	fz	0,023	0,030	0,036	0,050	0,061	0,070
	2	1 x D	0,5 x D	1 x D	60	–	80	fz	0,019	0,024	0,029	0,040	0,048	0,056
K	1	1 x D	0,5 x D	1 x D	120	–	150	fz	0,028	0,036	0,044	0,060	0,072	0,083
	2	1 x D	0,5 x D	1 x D	110	–	140	fz	0,023	0,030	0,036	0,050	0,061	0,070
	3	1 x D	0,5 x D	1 x D	110	–	130	fz	0,019	0,024	0,029	0,040	0,048	0,056
N	1	1 x D	0,5 x D	1 x D	500	–	2000	fz	0,040	0,050	0,060	0,080	0,100	0,120
	2	1 x D	0,5 x D	1 x D	500	–	1500	fz	0,036	0,045	0,054	0,072	0,090	0,108
	3	1 x D	0,5 x D	1 x D	250	–	1000	fz	0,036	0,045	0,054	0,072	0,090	0,108

NOTE: Lower value of cutting speed is used for high stock removal applications or for higher hardness (machinability) within group.
Higher value of cutting speed is used for finishing applications or for lower hardness (machinability) within group.