



MATERIAL	Hardness: ≤ 28 Rc (≤ 271 HBn)														
	SFM	Chip Load by Neck Diameter (IPT)													
		0.015	0.031	0.047	0.062	0.078	0.093	0.125	0.187	0.250	0.312	0.375	0.500	0.625	0.750
<b>ALUMINUM ALLOYS</b>															
Casting (2xx, 5xx, 7xx, 8xx)	750	.00017	.00034	.00052	.00068	.00086	.00102	.00138	.00206	.00275	.00343	.00413	.00550	.00688	.00825
Wrought (1xxx, 2xxx, 3xxx, 5xxx, 6xxx, 7xxx, 8xxx)	1000														
Casting - 3%-5% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	750														
Casting - 5%-8% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	700														
Casting - 8%-12% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	650	.00015	.00031	.00047	.00061	.00077	.00092	.00124	.00185	.00248	.00309	.00371	.00495	.00619	.00743
Casting - 12%-16% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	475														
Wrought - 5%-8% Si (4xxx)	1000														
Wrought - 8%-12% Si (4xxx)	800														
<b>MAGNESIUM ALLOYS</b>	1500	.00017	.00034	.00052	.00068	.00086	.00102	.00138	.00206	.00275	.00343	.00413	.00550	.00688	.00825
<b>ZINC ALLOYS</b>	800														
<b>COPPER ALLOYS</b>															
High Coppers - 90%+ (C1xxx)	225														
Brass (Copper Zinc alloys, C2xxx, C3xxx, C4xxx, C66400-C69800)	500														
Phosphor Bronzes (Copper Tin alloys, C5xxx)	225														
Aluminum Bronzes (Copper Aluminum alloys, C60600-C64200)	500	.00013	.00027	.00041	.00055	.00069	.00082	.00110	.00165	.00220	.00275	.00330	.00440	.00550	.00660
Silicon Bronzes (Copper Silicon alloys, C64700-C66100)	500														
Copper Nickels, Nickel Silvers (Copper Nickel alloys, C7xxx)	225														
Cast Copper Alloys (C83300-C86200, C86400-C87900, C9200-C95800, C97300-C97800, C99400-C99700)	550														



**Speeds & Feeds**

**Product Table: Dovetail Cutters**

**Series:** 164xx, 165xx, 166xx, 167xx 168xx, 270xx, 285xx, 615xx, 623xx, 634xx, 646xx, 651xx, 663xx, 8279xx, 8323xx, 8339xx, 8451xx, 8734xx, 8745xx, 8836xx, 8912xx, 8965xx, 9262xx, 9284xx, 9300xx, 9323xx, 9599xx, 9644xx, 9731xx, 9778xx, 9794xx, 9833xx, 9848xx, 9860xx, 9892xx, 9901xx, 9914xx, 9920xx, 9952xx

**Product Notes:**

True dovetail grooves (with trapezoidal shape) must be roughed out with end mill prior to using dovetail cutter

Posted Radial Passes reflect machining on one side of groove at full axial depth  
If machining on both sides of part, reduce Chip Loads (IPT) by 40%

When machining grooves with circular interpolation, reduce the Linear Feed (IPM) using the following formula:

$$\text{Adj Feed} = [(\text{Major Groove Dia} - \text{Cutter Dia}) / \text{Major Groove Dia}] \times \text{Linear Feed}$$

**General Notes:**

All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions. Chip loads reflect uncoated cutters and may be increased 5%-10% if coated. For ferrous materials with hardness ≤ 28 Rc, chip loads can be increased 5%-10%.

If you require additional information, Harvey Tool has a team of technical experts available to assist you through even the most challenging applications. Please contact us at **800-645-5609** or [Harveytech@harveyperformance.com](mailto:Harveytech@harveyperformance.com).

WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and other appropriate safety equipment in the vicinity of use.

MATERIAL	Hardness: 29-37 Rc (279-344 HBn)														
	SFM	Chip Load by Neck Diameter (IPT)													
		0.015	0.031	0.047	0.062	0.078	0.093	0.125	0.187	0.250	0.312	0.375	0.500	0.625	0.750
<b>CARBON STEELS</b>															
Free-Machining/Low Carbon steels, 10xx - 1029 & all 10Lxx, 11xx - 1139 & all 11Lxx, 12xx - 1215 & all 12Lxx	600	.00006	.00012	.00018	.00023	.00029	.00035	.00047	.00071	.00095	.00118	.00142	.00189	.00236	.00284
1030 - 1095, 1140 - 1151, 13xx, 15xx, 2xxx, 3xxx, 4xxx & 4xLxx, 5xxx & 5xLxx, 51xxx & 50Lxxx, 51xxx & 51Lxxx, 52xxx & 52Lxxx, 6xxx, 8xxx, 9xxx	200	.00005	.00011	.00016	.00021	.00027	.00032	.00043	.00065	.00086	.00108	.00130	.00173	.00216	.00259
<b>STAINLESS STEELS</b>															
203 EZ, 303 (all types), 416, 416Se, 416 Plus X, 420F, 420FSe, 430F, 430FSe, 440F, 440FSe	450	.00006	.00012	.00018	.00023	.00029	.00035	.00047	.00071	.00095	.00118	.00142	.00189	.00236	.00284
201, 202, 203, 205, 301, 302, 304, 304L, 308, 309, 310, 314, 316, 316L, 317, 321, 329, 330, 347, 348, 385, 403, 405, 409, 410, 413, 420, 429, 430, 434, 436, 442, 446, 501, 502	200	.00005	.00011	.00016	.00021	.00027	.00032	.00043	.00065	.00086	.00108	.00130	.00173	.00216	.00259
414, 431, 440A, 440B, 440C, 13-8, 15-5, 15-7, 17-4, 17-7	150	.00003	.00007	.00010	.00013	.00017	.00020	.00027	.00040	.00054	.00067	.00081	.00108	.00135	.00162
<b>TOOL STEELS</b>															
A, L, O, P, W series	200	.00005	.00011	.00016	.00021	.00027	.00032	.00043	.00065	.00086	.00108	.00130	.00173	.00216	.00259
D, H, M, T, S series	150	.00003	.00007	.00010	.00013	.00017	.00020	.00027	.00040	.00054	.00067	.00081	.00108	.00135	.00162
<b>TITANIUM ALLOYS</b>	150	.00003	.00007	.00010	.00013	.00017	.00020	.00027	.00040	.00054	.00067	.00081	.00108	.00135	.00162
<b>HIGH TEMP ALLOYS</b>															
Inconel, Hastelloy, Waspalloy, Monel, Nimonic, Haynes, Discoloy, Incoloy	70	.00003	.00007	.00010	.00013	.00017	.00020	.00027	.00040	.00054	.00067	.00081	.00108	.00135	.00162

MATERIAL	Hardness: 38-45 Rc (353-421 HBn)														
	SFM	Chip Load by Neck Diameter (IPT)													
		0.015	0.031	0.047	0.062	0.078	0.093	0.125	0.187	0.250	0.312	0.375	0.500	0.625	0.750
	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
	200	.00003	.00005	.00008	.00011	.00013	.00016	.00022	.00032	.00043	.00054	.00065	.00086	.00108	.00130
	150	.00002	.00003	.00005	.00007	.00008	.00010	.00014	.00020	.00027	.00034	.00041	.00054	.00068	.00081
	200	.00003	.00005	.00008	.00011	.00013	.00016	.00022	.00032	.00043	.00054	.00065	.00086	.00108	.00130
	150	.00002	.00003	.00005	.00007	.00008	.00010	.00014	.00020	.00027	.00034	.00041	.00054	.00068	.00081
	150	.00002	.00003	.00005	.00007	.00008	.00010	.00014	.00020	.00027	.00034	.00041	.00054	.00068	.00081
	70	.00002	.00003	.00005	.00007	.00008	.00010	.00014	.00020	.00027	.00034	.00041	.00054	.00068	.00081