

## GOmill GP • 4SE..IS-IR • 4 Flute • Short • Regular



EURING CURING

FIRST MILLING

FIRST HOLEMAKING

	Side Milling (A) and Slotting (B)			g (A) g (B)	К	C633	М	Recommended feed per tooth (IPT = inch/th) for side milling (A). For slotting (B), reduce IPT by 20%.														
	A		B	Cutting Speed – vc SFM			D1 – Diameter															
laterial Group		ар	ae	ар	min		max	inch	1/64 .0156	1/32 .0313	1/16 .0625	5/64 .0781	3/32 .0938	1/8 .1250	3/16 .1875	1/4 .2500	5/16 .3125	3/8 .3750	1/2 .5000	5/8 .6250	3/4 .7500	1 1.0000
	0	Ap1 max	0.1 x D	0.5 x D	490	-	660	IPT	.0001	.0002	.0004	.0005	.0007	.0009	.0014	.0018	.0023	.0027	.0034	.0040	.0044	.0049
	1	Ap1 max	0.1 x D	0.5 x D	490	-	660	IPT	.0001	.0002	.0004	.0005	.0007	.0009	.0014	.0018	.0023	.0027	.0034	.0040	.0044	.0049
	2	Ap1 max	0.1 x D	0.5 x D	460	-	620	IPT	.0001	.0002	.0004	.0005	.0007	.0009	.0014	.0018	.0023	.0027	.0034	.0040	.0044	.0049
	3	Ap1 max	0.1 x D	0.5 x D	390	_	520	IPT	.0001	.0002	.0004	.0004	.0005	.0007	.0011	.0015	.0020	.0023	.0029	.0034	.0039	.0045
	4	Ap1 max	0.1 x D	0.5 x D	300	-	490	IPT	.0001	.0002	.0003	.0004	.0005	.0007	.0010	.0014	.0018	.0020	.0026	.0030	.0034	.0039
Λ	1	Ap1 max	0.1 x D	0.5 x D	300	-	380	IPT	.0001	.0002	.0004	.0004	.0005	.0007	.0011	.0015	.0020	.0023	.0029	.0034	.0039	.0045
	2	Ap1 max	0.1 x D	0.5 x D	200	_	260	IPT	.0001	.0002	.0003	.0004	.0004	.0006	.0009	.0012	.0016	.0018	.0023	.0027	.0031	.0036
ĸ	1	Ap1 max	0.1 x D	0.5 x D	390	-	490	IPT	.0001	.0002	.0004	.0005	.0007	.0009	.0014	.0018	.0023	.0027	.0034	.0040	.0044	.0049
	2	Ap1 max	0.1 x D	0.5 x D	360	-	460	IPT	.0001	.0002	.0004	.0004	.0005	.0007	.0011	.0015	.0020	.0023	.0029	.0034	.0039	.0045
	1	Ap1 max	0.1 x D	0.5 x D	300	-	380	IPT	.0002	.0003	.0006	.0008	.0009	.0013	.0019	.0025	.0031	.0038	.0050	.0063	.0075	.0100
١	2	Ap1 max	0.1 x D	0.5 x D	200	_	260	IPT	.0001	.0003	.0005	.0006	.0008	.0010	.0015	.0020	.0025	.0030	.0040	.0050	.0060	.0080
	4	Ap1 max	0.1 x D	0.5 x D	390	-	490	IPT	.0001	.0003	.0006	.0007	.0008	.0011	.0017	.0023	.0028	.0034	.0045	.0056	.0068	.0090

NOTE: Lower value of cutting speed is used for high stock removal applications or for higher hardness (machinability) within group. Higher value of cutting speed is used for finishing applications or for lower hardness (machinability) within group. Above parameters are based on ideal conditions. For smaller taper machining centers, please adjust parameters accordingly on >1/2" diameter.

## GOmill GP • 4SE..IL • 4 Flute • Long

		100 - 100 - 100 - 100 - 100 - 100 - 100 - 100 - 100 - 100 - 100 - 100 - 100 - 100 - 100 - 100 - 100 - 100 - 100																
	Side Milling (A)			KC633M			Recommended feed per tooth (IPT = inch/th) for side milling (A).											
	A		Cutting Speed – vc SFM			D1 – Diameter												
laterial								3/32	1/8	3/16	1/4	5/16	3/8	1/2	5/8	3/4	1	
Gro	oup	ар	ae	min		max	inch	.0938	.1250	.1875	.2500	.3125	.3750	.5000	.6250	.7500	1.0000	
	0	Ap1 max	0.1 x D	490	-	660	IPT	.0007	.0009	.0014	.0018	.0023	.0027	.0034	.0040	.0044	.0049	
	1	Ap1 max	0.1 x D	490	-	660	IPT	.0007	.0009	.0014	.0018	.0023	.0027	.0034	.0040	.0044	.0049	
Ρ	2	Ap1 max	0.1 x D	460	-	620	IPT	.0007	.0009	.0014	.0018	.0023	.0027	.0034	.0040	.0044	.0049	
	3	Ap1 max	0.1 x D	390	-	520	IPT	.0005	.0007	.0011	.0015	.0020	.0023	.0029	.0034	.0039	.0045	
	4	Ap1 max	0.1 x D	300	-	490	IPT	.0005	.0007	.0010	.0014	.0018	.0020	.0026	.0030	.0034	.0039	
	1	Ap1 max	0.1 x D	300	_	380	IPT	.0005	.0007	.0011	.0015	.0020	.0023	.0029	.0034	.0039	.0045	
VI	2	Ap1 max	0.1 x D	200	-	260	IPT	.0004	.0006	.0009	.0012	.0016	.0018	.0023	.0027	.0031	.0036	
к	1	Ap1 max	0.1 x D	390	_	490	IPT	.0007	.0009	.0014	.0018	.0023	.0027	.0034	.0040	.0044	.0049	
	2	Ap1 max	0.1 x D	360	-	460	IPT	.0005	.0007	.0011	.0015	.0020	.0023	.0029	.0034	.0039	.0045	
	1	Ap1 max	0.1 x D	820	-	3250	IPT	.0009	.0013	.0019	.0025	.0031	.0038	.0050	.0063	.0075	.0100	
N	2	Ap1 max	0.1 x D	820	_	2450	IPT	.0008	.0010	.0015	.0020	.0025	.0030	.0040	.0050	.0060	.0080	
	4	Ap1 max	0.1 x D	820	-	2450	IPT	.0008	.0011	.0017	.0023	.0028	.0034	.0045	.0056	.0068	.0090	

NOTE: Lower value of cutting speed is used for high stock removal applications or for higher hardness (machinability) within group.

Higher value of cutting speed is used for finishing applications or for lower hardness (machinability) within group. Above parameters are based on ideal conditions. For smaller taper machining centers, please adjust parameters accordingly on >1/2" diameter.

