

$$\text{RPM} = \frac{\text{SFM}}{\text{DIAM. in.}} \times 3.82 \quad \text{IPM} = \text{IPR} \times \text{RPM}$$

$$\frac{\text{HOLE DEPTH in.}}{\text{IPM}} \times 60 = \text{Cut Time} \quad \text{mm} = \text{in.} \times 25.40$$

$$\text{m/min.} = \text{SFM} \div 3.28 \quad \text{Bar} = \text{PSI} \div 14.50$$

$$\text{mm/rev.} = \text{IPR} \times 25.40 \quad \text{Liter} = \text{Gal.} \div 3.79$$

# Series # 235

Material group	Hardness	SFM	Feed Rate - IPR									
			1/16 in. 1.590 mm	1/8 in. 3.170 mm	1/4 in. 6.350 mm	3/8 in. 9.520 mm	1/2 in. 12.700 mm	5/8 in. 15.870 mm	3/4 in. 19.050 mm	1 in. 25.400 mm	1 1/4 in. 31.750 mm	1 1/2 in. 38.100 mm
Common structural steels	≤100 Bhn	70	0.0015	0.0040	0.0065	0.0080	0.0100	0.0100	•	•	•	•
	>100-260 Bhn	55	0.0012	0.0030	0.0050	0.0065	0.0080	•	•	•	•	•
Free-cutting steels	≤24 Rc	70	0.0015	0.0040	0.0065	0.0080	0.0100	•	•	•	•	•
	>24-30 Rc	55	0.0012	0.0030	0.0050	0.0065	0.0080	•	•	•	•	•
Unalloyed heat-treatable steels	≤16 Rc	70	0.0012	0.0030	0.0050	0.0065	0.0080	•	•	•	•	•
	16-24 Rc	55	0.0012	0.0030	0.0050	0.0065	0.0080	•	•	•	•	•
	24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
Alloyed heat-treatable steels	24-30 Rc	35	0.0010	0.0025	0.0040	0.0050	0.0065	•	•	•	•	•
	>30-38 Rc	•	•	•	•	•	•	•	•	•	•	•
Unalloyed case hardened steels	≤230 Bhn	70	0.0015	0.0040	0.0065	0.0080	0.0100	•	•	•	•	•
Alloyed case hardened steels	24-30 Rc	30	0.0010	0.0025	0.0040	0.0050	0.0065	•	•	•	•	•
	>30-38 Rc	•	•	•	•	•	•	•	•	•	•	•
Nitriding steels	≥24-30 Rc	25	0.0010	0.0025	0.0040	0.0050	0.0065	•	•	•	•	•
	>30-38 Rc	•	•	•	•	•	•	•	•	•	•	•
Tool steels	≤24 Rc	35	0.0010	0.0025	0.0040	0.0050	0.0065	•	•	•	•	•
	>24-30 Rc	15	0.0007	0.0020	0.0030	0.0040	0.0050	•	•	•	•	•
High speed steels	≥14-30 Rc	15	0.0007	0.0020	0.0030	0.0040	0.0050	•	•	•	•	•
Spring steels	≤330 Bhn	•	•	•	•	•	•	•	•	•	•	•
Stainless steels, sulphured austenitic martensitic	≤24 Rc	25	0.0010	0.0025	0.0040	0.0050	0.0065	•	•	•	•	•
	≤24 Rc	•	•	•	•	•	•	•	•	•	•	•
	≤24 Rc	•	•	•	•	•	•	•	•	•	•	•
Hardened steels	≤40-48 Rc	•	•	•	•	•	•	•	•	•	•	•
	>48-60 Rc	•	•	•	•	•	•	•	•	•	•	•
Special alloys	≤38 Rc	•	•	•	•	•	•	•	•	•	•	•
Cast iron	≤240 Bhn	70	0.0015	0.0040	0.0065	0.0080	0.0100	•	•	•	•	•
	<300 Bhn	55	0.0015	0.0040	0.0065	0.0080	0.0100	•	•	•	•	•
Spheroidal graphite iron and malleable cast iron	≤240 Bhn	65	0.0015	0.0040	0.0065	0.0080	0.0100	•	•	•	•	•
	<300 Bhn	45	0.0015	0.0040	0.0065	0.0080	0.0100	•	•	•	•	•
Chilled cast iron	≤350 Bhn	•	•	•	•	•	•	•	•	•	•	•
Ti and Ti-alloys	≤24 Rc	•	•	•	•	•	•	•	•	•	•	•
	>24-38 Rc	•	•	•	•	•	•	•	•	•	•	•
Aluminium and Al-alloys	≤120 Bhn	•	•	•	•	•	•	•	•	•	•	•
Al wrought alloys	≤150 Bhn	•	•	•	•	•	•	•	•	•	•	•
Al cast alloys ≤ 10 % Si > 10 % Si	≤200 Bhn	145	0.0017	0.0050	0.0080	0.0100	0.0125	•	•	•	•	•
	≤200 Bhn	115	0.0015	0.0040	0.0065	0.0080	0.0100	•	•	•	•	•
Magnesium alloys	≤150 Bhn	180	0.0015	0.0040	0.0065	0.0080	0.0100	•	•	•	•	•
Copper, low-alloyed	≤120 Bhn	70	0.0012	0.0030	0.0050	0.0065	0.0080	•	•	•	•	•
Brass, short-chipping long-chipping	≤200 Bhn	145	0.0012	0.0030	0.0050	0.0065	0.0080	•	•	•	•	•
	≤200 Bhn	90	0.0012	0.0030	0.0050	0.0065	0.0080	•	•	•	•	•
Bronze, short-chipping	≤200 Bhn	70	0.0010	0.0025	0.0040	0.0050	0.0065	•	•	•	•	•
	>200-260 Bhn	65	0.0010	0.0025	0.0040	0.0050	0.0065	•	•	•	•	•
Bronze, long-chipping	≤24 Rc	55	0.0010	0.0025	0.0040	0.0050	0.0065	•	•	•	•	•
	>24-30 Rc	45	0.0010	0.0025	0.0040	0.0050	0.0065	•	•	•	•	•
Duroplastics	-	35	0.0010	0.0025	0.0040	0.0050	0.0065	•	•	•	•	•
Thermoplastics	-	55	0.0012	0.0030	0.0050	0.0065	0.0080	•	•	•	•	•
Reinforced plastics - Kevlar	-	•	•	•	•	•	•	•	•	•	•	•
Reinforced plastics - GFK / CFK	-	•	•	•	•	•	•	•	•	•	•	•

# Series # 245

Material group	Hardness	SFM	Feed Rate - IPR									
			1/16 in. 1.590 mm	1/8 in. 3.170 mm	1/4 in. 6.350 mm	3/8 in. 9.520 mm	1/2 in. 12.700 mm	5/8 in. 15.870 mm	3/4 in. 19.050 mm	1 in. 25.400 mm	1 1/4 in. 31.750 mm	1 1/2 in. 38.100 mm
Common structural steels	≤100 Bhn	100	•	0.0050	0.0080	0.0100	0.0125	0.0140	0.0160	0.0200	0.0245	•
	>100-260 Bhn	80	•	0.0040	0.0065	0.0080	0.0100	0.0110	0.0125	0.0160	0.0200	•
Free-cutting steels	≤24 Rc	100	•	0.0050	0.0080	0.0100	0.0125	0.0140	0.0160	0.0200	0.0245	•
	>24-30 Rc	80	•	0.0040	0.0065	0.0080	0.0100	0.0110	0.0125	0.0160	0.0200	•
Unalloyed heat-treatable steels	≤16 Rc	100	•	0.0040	0.0065	0.0080	0.0100	0.0110	0.0125	0.0160	0.0200	•
	16-24 Rc	80	•	0.0040	0.0065	0.0080	0.0100	0.0110	0.0125	0.0160	0.0200	•
	24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
Alloyed heat-treatable steels	24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
	>30-38 Rc	•	•	•	•	•	•	•	•	•	•	•
Unalloyed case hardened steels	≤230 Bhn	100	•	0.0050	0.0080	0.0100	0.0125	0.0140	0.0160	0.0200	0.0245	•
Alloyed case hardened steels	24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
	>30-38 Rc	•	•	•	•	•	•	•	•	•	•	•
Nitriding steels	≥24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
	>30-38 Rc	•	•	•	•	•	•	•	•	•	•	•
Tool steels	≤24 Rc	50	•	0.0030	0.0050	0.0065	0.0080	0.0090	0.0100	0.0125	0.0160	•
	>24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
High speed steels	≥14-30 Rc	•	•	•	•	•	•	•	•	•	•	•
Spring steels	≤330 Bhn	•	•	•	•	•	•	•	•	•	•	•
Stainless steels, sulphured austenitic martensitic	≤24 Rc	•	•	•	•	•	•	•	•	•	•	•
	≤24 Rc	•	•	•	•	•	•	•	•	•	•	•
	≤24 Rc	•	•	•	•	•	•	•	•	•	•	•
Hardened steels	≤40-48 Rc	•	•	•	•	•	•	•	•	•	•	•
	>48-60 Rc	•	•	•	•	•	•	•	•	•	•	•
Special alloys	≤38 Rc	•	•	•	•	•	•	•	•	•	•	•
Cast iron	≤240 Bhn	100	•	0.0050	0.0080	0.0100	0.0125	0.0140	0.0160	0.0200	0.0245	•
	<300 Bhn	80	•	0.0050	0.0080	0.0100	0.0125	0.0140	0.0160	0.0200	0.0245	•
Spheroidal graphite iron and malleable cast iron	≤240 Bhn	90	•	0.0050	0.0080	0.0100	0.0125	0.0140	0.0160	0.0200	0.0245	•
	<300 Bhn	65	•	0.0050	0.0080	0.0100	0.0125	0.0140	0.0160	0.0200	0.0245	•
Chilled cast iron	≤350 Bhn	•	•	•	•	•	•	•	•	•	•	•
Ti and Ti-alloys	≤24 Rc	•	•	•	•	•	•	•	•	•	•	•
	>24-38 Rc	•	•	•	•	•	•	•	•	•	•	•
Aluminium and Al-alloys	≤120 Bhn	•	•	•	•	•	•	•	•	•	•	•
Al wrought alloys	≤150 Bhn	•	•	•	•	•	•	•	•	•	•	•
Al cast alloys ≤ 10 % Si > 10 % Si	≤200 Bhn	205	•	0.0065	0.0100	0.0125	0.0160	0.0180	0.0200	0.0245	0.0290	•
	≤200 Bhn	160	•	0.0050	0.0080	0.0100	0.0125	0.0140	0.0160	0.0200	0.0245	•
Magnesium alloys	≤150 Bhn	260	•	0.0050	0.0080	0.0100	0.0125	0.0140	0.0160	0.0200	0.0245	•
Copper, low-alloyed	≤120 Bhn	100	•	0.0040	0.0065	0.0080	0.0100	0.0110	0.0125	0.0160	0.0200	•
Brass, short-chipping long-chipping	≤200 Bhn	•	•	•	•	•	•	•	•	•	•	•
	≤200 Bhn	130	•	0.0040	0.0065	0.0080	0.0100	0.0110	0.0125	0.0160	0.0200	•
Bronze, short-chipping	≤200 Bhn	100	•	0.0030	0.0050	0.0065	0.0080	0.0090	0.0100	0.0125	0.0160	•
	>200-260 Bhn	90	•	0.0030	0.0050	0.0065	0.0080	0.0090	0.0100	0.0125	0.0160	•
Bronze, long-chipping	≤24 Rc	80	•	0.0030	0.0050	0.0065	0.0080	0.0090	0.0100	0.0125	0.0160	•
	>24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
Duroplastics	-	50	•	0.0030	0.0050	0.0065	0.0080	0.0090	0.0100	0.0125	0.0160	•
Thermoplastics	-	80	•	0.0040	0.0065	0.0080	0.0100	0.0110	0.0125	0.0160	0.0200	•
Reinforced plastics - Kevlar	-	•	•	•	•	•	•	•	•	•	•	•
Reinforced plastics - GFK / CFK	-	•	•	•	•	•	•	•	•	•	•	•