

Material group	Hardness		SFM	Feed Rate - IPR								
	HRC	BHN		.5 mm	1.0 mm	2.0 mm	2.5 mm	3.15 mm	4.0 mm	5.0 mm	6.3 mm	8 mm
Common structural steels	-	≤ 150	100	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
	≤ 32	≤ 301	80	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
Free-cutting steels	≤ 25	≤ 255	100	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
	≤ 32	≤ 301	100	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
Unalloyed heat-treatable steels	≤ 20	≤ 220	80	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
	≤ 25	≤ 255	65	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
Alloyed heat-treatable steels	≤ 32	≤ 301	50	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
	≤ 43	≤ 402	25	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
Unalloyed case hardened steels	≤ 25	≤ 255	80	0.0004	0.0006	0.0020	0.0025	0.0031	0.0039	0.0039	0.0049	0.0063
Alloyed case hardened steels	≤ 32	≤ 301	50	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
Nitriding steels	≤ 32	≤ 301	35	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
	≤ 43	≤ 402	25	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
Tool steels	≤ 25	≤ 255	35	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
	≤ 43	≤ 402	20	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
High speed steels	≤ 43	≤ 402	20	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
Spring steels	≤ 38	≤ 354	15	0.0002	0.0003	0.0010	0.0013	0.0016	0.0020	0.0020	0.0025	0.0031
Hardened steels	≤ 48	≤ 460										
	-	-										
Stainless steels, sulphured	≤ 28	≤ 273	35	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
	≤ 36	≤ 337	25	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
austenitic	≤ 36	≤ 337	25	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
	≤ 46	≤ 435	20	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
martensitic	≤ 46	≤ 435	20	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
	-	-										
Cast iron	≤ 23	≤ 242	65	0.0005	0.0007	0.0025	0.0031	0.0039	0.0049	0.0049	0.0063	0.0079
	≤ 38	≤ 354	65	0.0004	0.0006	0.0020	0.0025	0.0031	0.0039	0.0039	0.0049	0.0063
Spheroidal graphite iron and malleable cast iron	≤ 23	≤ 242	80	0.0005	0.0007	0.0025	0.0031	0.0039	0.0049	0.0049	0.0063	0.0079
	≤ 38	≤ 354	65	0.0004	0.0006	0.0020	0.0025	0.0031	0.0039	0.0039	0.0049	0.0063
Chilled cast iron	≤ 38	≤ 354										
New cast materials GGV	≤ 20	≤ 220										
New cast materials ADI	≤ 32	≤ 301										
	≤ 43	≤ 402										
Special alloys	≤ 54	≤ 549	10	0.0002	0.0002	0.0008	0.0010	0.0013	0.0016	0.0016	0.0020	0.0025
Ti and Ti-alloys	≤ 25	≤ 255	15	0.0002	0.0003	0.0010	0.0013	0.0016	0.0020	0.0020	0.0025	0.0031
	≤ 43	≤ 402	15	0.0002	0.0003	0.0010	0.0013	0.0016	0.0020	0.0020	0.0025	0.0031
Aluminium and Al-alloys	-	≤ 120	230	0.0006	0.0008	0.0031	0.0039	0.0049	0.0063	0.0063	0.0079	0.0098
Al wrought alloys	-	≤ 200	230	0.0006	0.0008	0.0031	0.0039	0.0049	0.0063	0.0063	0.0079	0.0098
Al cast alloys ≤ 10 % Si	-	≤ 180	130	0.0005	0.0007	0.0025	0.0031	0.0039	0.0049	0.0049	0.0063	0.0079
	-	≤ 180	130	0.0005	0.0007	0.0025	0.0031	0.0039	0.0049	0.0049	0.0063	0.0079
≤ 24 % Si	-	≤ 180	130	0.0005	0.0007	0.0025	0.0031	0.0039	0.0049	0.0049	0.0063	0.0079
Magnesium alloys	-	≤ 120	195	0.0005	0.0007	0.0025	0.0031	0.0039	0.0049	0.0049	0.0063	0.0079
Copper, low-alloyed	-	≤ 150	165	0.0004	0.0006	0.0020	0.0025	0.0031	0.0039	0.0039	0.0049	0.0063
Brass, short-chipping	-	≤ 180	195	0.0004	0.0006	0.0020	0.0025	0.0031	0.0039	0.0039	0.0049	0.0063
	-	≤ 180	130	0.0004	0.0006	0.0020	0.0025	0.0031	0.0039	0.0039	0.0049	0.0063
Bronze, short-chipping	-	≤ 180	100	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
	≤ 25	≤ 255	80	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
Bronze, long-chipping	≤ 25	≤ 255	50	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
	≤ 32	≤ 301	50	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
Duroplastics			50	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
Thermoplastics			80	0.0004	0.0006	0.0020	0.0025	0.0031	0.0039	0.0039	0.0049	0.0063
Reinforced plastics - Kevlar												
Reinforced plastics - GFK / CFK												

Material group	Hardness		SFM	Feed Rate - IPR								
	HRC	BHN		.5 mm	1.0 mm	2.0 mm	2.5 mm	3.15 mm	4.0 mm	5.0 mm	6.3 mm	8 mm
Common structural steels	-	≤ 150	100	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
	≤ 32	≤ 301	80	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
Free-cutting steels	≤ 25	≤ 255	100	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
	≤ 32	≤ 301	100	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
Unalloyed heat-treatable steels	≤ 20	≤ 220	80	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
	≤ 25	≤ 255	65	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
Alloyed heat-treatable steels	≤ 32	≤ 301	50	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
	≤ 43	≤ 402	25	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
Unalloyed case hardened steels	≤ 25	≤ 255	80	0.0004	0.0006	0.0020	0.0025	0.0031	0.0039	0.0039	0.0049	0.0063
Alloyed case hardened steels	≤ 32	≤ 301	50	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
Nitriding steels	≤ 32	≤ 301	35	0.0003	0.0006	0.0016	0.0020	0.0025	0.0031	0.0031	0.0039	0.0049
	≤ 43	≤ 402	25	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
Tool steels	≤ 25	≤ 255	35	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
	≤ 43	≤ 402	20	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
High speed steels	≤ 43	≤ 402	20	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
Spring steels	≤ 38	≤ 354	15	0.0002	0.0003	0.0010	0.0013	0.0016	0.0020	0.0020	0.0025	0.0031
Hardened steels	≤ 48	≤ 460										
	-	-										
Stainless steels, sulphured	≤ 28	≤ 273	35	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
	≤ 36	≤ 337	25	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
austenitic	≤ 36	≤ 337	25	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
	≤ 46	≤ 435	20	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
martensitic	≤ 46	≤ 435	20	0.0003	0.0005	0.0013	0.0016	0.0020	0.0025	0.0025	0.0031	0.0039
	-	-										
Cast iron	≤ 23	≤ 242	65	0.0005	0.0007	0.0025	0.0031	0.0039	0.0049	0.0049	0.0063	0.0079
	≤ 38	≤ 354	65	0.0004	0.0006	0.0020	0.0025	0.0031	0.0039	0.0039	0.0049	0.0063
Spheroidal graphite iron and malleable cast iron	≤ 23	≤ 242	80	0.0005	0.0007	0.0025	0.0031	0.0039	0.0049	0.0049	0.0063	0.0079
	≤ 38	≤ 354	65	0.0004	0.0006	0.0020	0.0025	0.0031	0.0039	0.0039	0.0049	0.0063
Chilled cast iron	≤ 38	≤ 354										
New cast materials GGV	≤ 20	≤ 220										
New cast materials ADI	≤ 32	≤ 301										
	≤ 43	≤ 402										
Special alloys	≤ 54	≤ 549	10	0.0002	0.0002	0.0008	0.0010	0.0013	0.0016	0.0016	0.0020	0.0025
Ti and Ti-alloys	≤ 25	≤ 255	15	0.0002	0.0003	0.0010	0.0013	0.				