

Product Table: Variable Helix End Mills for High Temp Alloys - Ball **Characteristics:** 3x Length of Cut, 3 Flutes

Series: 9705xx-C6, 9753xx-C6 and Items #970600-C6, #970602-C6

Material	Hardness (HBn)	SFM	Chip Load (IPT) By Cutter Diameter													Depth of Cut	
				0.015	0.031	0.047	0.062	0.078	0.093	0.125	0.187	0.250	0.312	0.375	0.500	Radial	Axial
Stainless Steels: 40x, 41x, 42x, 43x, 44x, 13-8, 15-5, 15-7, 17-4, 17-7	275 - 300	160	Slotting	.00005	.00011	.00016	.00021	.00027	.00032	.00043	.00065	.00087	.00114	.00136	.00182	1x Dia	.4x Dia
	300 - 350	140															
Tool Steels: D, H, M, T, S series	350 - 400	100															
	400 - 425	80															
Titanium: All alloys	275 - 300	200	Roughing	.00007	.00014	.00021	.00027	.00034	.00041	.00055	.00082	.00110	.00144	.00174	.00232	.4x Dia	.5x7x Dia
	300 - 350	125															
	350 - 400	75	75 Finishing	.00009	.00018	.00027	.00036	.00045	.00054	.00072	.00108	.00144	.00189	.00227	.00303	.1x Dia	.5x - 1x Dia
	400 - 425	75															
Nickel Alloys: Inconel, Hastelloy, Waspalloy, Monel, Nimonic, Haynes, Discoloy, Incoloy	275 - 300	80															
	300 - 350	60	50 Max	.00010	.00021	.00033	.00043	.00054	.00064	.00087	.00130	.00173	.00227	.00273	.00364	-	-
	350 - 400	50															
	400 - 425	40															

Please note:

All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions. If less than minimum Axial or Radial DOC values are used, increased feed rates are possible. If greater than maximum Axial or Radial DOC values are used, decreased feed rates may be needed. If you require additional information, Harvey Tool has a team of technical experts available to assist you through even the most challenging applications. Please contact us at 800-645-5609 or Harveytech@harveyperformance.com.

WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and other appropriate safety equipment in the vicinity of use.