

■ HARVI I • HPRSHV • Unequal Flute Spacing • Extended Reach

Material Group	Side Milling (A) and Slotting (B)		KCPM15		Recommended feed per tooth (IPT = inch/th) for side milling (A). For slotting (B), reduce IPT by 20%.							
	A		B		Cutting Speed – vc SFM		D1 – Diameter					
	ap	ae	ap		min	max	frac.	1/2	5/8	3/4	1	
							dec.	.500	.625	.750	1.000	
P	1	0.75 x D	0.5 x D	0.75 x D	500	650	IPT	.0035	.0039	.0043	.0050	
	2	0.75 x D	0.5 x D	0.75 x D	450	625	IPT	.0035	.0039	.0043	.0050	
	3	0.75 x D	0.5 x D	0.75 x D	400	525	IPT	.0029	.0034	.0038	.0046	
	4	0.75 x D	0.5 x D	0.5 x D	300	475	IPT	.0026	.0030	.0033	.0039	
	5	1.5 x D	0.5 x D	0.75 x D	200	325	IPT	.0023	.0027	.0030	.0036	
	6	0.75 x D	0.5 x D	0.5 x D	150	225	IPT	.0019	.0022	.0024	.0028	
M	1	0.75 x D	0.5 x D	0.75 x D	260	330	IPT	.0029	.0034	.0038	.0046	
	2	0.75 x D	0.5 x D	0.75 x D	200	260	IPT	.0023	.0027	.0030	.0036	
	3	0.75 x D	0.5 x D	0.75 x D	200	260	IPT	.0019	.0022	.0024	.0028	
K	1	0.75 x D	0.5 x D	0.75 x D	390	520	IPT	.0035	.0039	.0043	.0050	
	2	0.75 x D	0.5 x D	0.75 x D	360	460	IPT	.0029	.0034	.0038	.0046	
	3	0.75 x D	0.5 x D	0.75 x D	330	430	IPT	.0023	.0027	.0030	.0036	

NOTE: Those guidelines may require variations to achieve optimum results.
 For tools with reach > 3 x D, reduce fz by 20%.
 For tools with reach > 5 x D, reduce fz by 30%.
 For tools with reach > 10 x D, reduce vc and fz by 30%.

■ HARVI I • HPHVBN • 4 Flute with Extended Length-of-Cut • Ball Nose

High-Performance Solid Carbide End Mills

Material Group	Side Milling (A) and Slotting (B)		KCPM15		Recommended feed per tooth (IPT = inch/th) for side milling (A). For slotting (B), reduce IPT by 20%.												
	A		B		Cutting Speed – vc SFM		D1 – Diameter										
	ap	ae	ap		min	max	frac.	1/8	3/16	1/4	5/16	3/8	7/16	1/2	5/8	3/4	1
							dec.	.125	.188	.250	.313	.375	.438	.500	.625	.750	1.000
P	0	1.25 x D	0.5 x D	1 x D	490	660	IPT	.0009	.0013	.0018	.0023	.0027	.0031	.0034	.0039	.0044	.0049
	1	1.25 x D	0.5 x D	1 x D	490	660	IPT	.0009	.0013	.0018	.0023	.0027	.0031	.0034	.0039	.0044	.0049
	2	1.25 x D	0.5 x D	1 x D	460	620	IPT	.0009	.0013	.0018	.0023	.0027	.0031	.0034	.0039	.0044	.0049
	3	1.25 x D	0.5 x D	1 x D	390	520	IPT	.0007	.0011	.0015	.0020	.0023	.0026	.0029	.0034	.0039	.0045
	4	1.25 x D	0.5 x D	0.75 x D	300	490	IPT	.0007	.0010	.0014	.0017	.0020	.0023	.0026	.0030	.0034	.0039
	5	1.25 x D	0.5 x D	1 x D	200	330	IPT	.0006	.0009	.0012	.0016	.0018	.0021	.0023	.0027	.0031	.0036
M	1	1.25 x D	0.5 x D	1 x D	300	380	IPT	.0007	.0011	.0015	.0020	.0023	.0026	.0029	.0034	.0039	.0045
	2	1.25 x D	0.5 x D	1 x D	200	260	IPT	.0006	.0009	.0012	.0016	.0018	.0021	.0023	.0027	.0031	.0036
	3	1.25 x D	0.5 x D	1 x D	200	230	IPT	.0005	.0008	.0010	.0013	.0015	.0017	.0019	.0022	.0025	.0028
K	1	1.25 x D	0.5 x D	1 x D	390	490	IPT	.0009	.0013	.0018	.0023	.0027	.0031	.0034	.0039	.0044	.0049
	2	1.25 x D	0.5 x D	1 x D	360	460	IPT	.0007	.0011	.0015	.0020	.0023	.0026	.0029	.0034	.0039	.0045
	3	1.25 x D	0.5 x D	1 x D	360	430	IPT	.0006	.0009	.0012	.0016	.0018	.0021	.0023	.0027	.0031	.0036
S	1	1 x D	0.3 x D	0.3 x D	160	300	IPT	.0007	.0011	.0015	.0020	.0023	.0026	.0029	.0034	.0039	.0045
	2	1 x D	0.3 x D	0.3 x D	80	130	IPT	.0004	.0006	.0008	.0010	.0012	.0014	.0015	.0018	.0021	.0024
	3	1.25 x D	0.3 x D	0.3 x D	80	130	IPT	.0004	.0006	.0008	.0010	.0012	.0014	.0015	.0018	.0021	.0024
	4	1.25 x D	0.5 x D	1 x D	160	200	IPT	.0005	.0008	.0011	.0014	.0017	.0019	.0021	.0025	.0028	.0033
H	1	1.25 x D	0.5 x D	0.75 x D	260	460	IPT	.0007	.0010	.0014	.0017	.0020	.0023	.0026	.0030	.0034	.0039

NOTE: These guidelines may require variations to achieve optimum results.
 Lower value of cutting speed is used for high stock removal applications or for higher hardness (machinability) within group.
 Higher value of cutting speed is used for finishing applications or for lower hardness (machinability) within group.
 Above parameters are based on ideal conditions. For smaller taper machining centers, please adjust parameters accordingly on >1/2" diameter.