STRAIGHT SHANK DRILLS/TAPER SHANK DRILLS

GSD GWSS GWSL GTD GWTS GTTD

TiN coated drills

RECOMMENDED CUTTING CONDITIONS

Work material	Structural steel SS Carbon steel S-C (—25HRC)		Alloy steel SCM Tool steel SK (—35HRC)		Alloy steel SCM Die steel SKD (—40HRC)		Cast iron FC	
Dia. DC (mm)	Revolution (min^{-1})	Feed rate (mm/rev)	Revolution (min^{-1})	Feed rate (mm/rev)	Revolution (min^{-1})	Feed rate (mm/rev)	Revolution (min^{-1})	Feed rate (mm/rev)
0.5	8000	0.01	7000	0.008	6000	0.005	8000	0.01
1.0	6000	0.02	5500	0.01	4500	0.008	6000	0.02
2.0	4700	0.05	3600	0.03	2400	0.02	4700	0.05
3.0	3200	0.10	2400	0.08	1800	0.05	3500	0.10
6.0	1600	0.18	1200	0.15	900	0.13	1750	0.18
8.0	1200	0.20	900	0.18	680	0.15	1300	0.20
10.0	960	0.22	720	0.20	550	0.18	1100	0.22
12.0	800	0.24	600	0.22	450	0.20	880	0.24
15.0	630	0.28	480	0.24	350	0.22	700	0.28
20.0	470	0.33	360	0.26	260	0.24	530	0.33
25.0	380	0.36	290	0.28	210	0.26	420	0.36
30.0	310	0.40	240	0.30	180	0.28	330	0.40

Work material	Stainless steel				Copper alloy, Brass		Aluminium alloy	
	Martensitic Ferritic AISI 430		Austenitic AISI 304 Precipitation hardening ASTM 630					
Dia. DC (mm)	Revolution (min^{-1})	Feed rate (mm/rev)	Revolution (min^{-1})	Feed rate (mm/rev)	Revolution (min^{-1})	Feed rate (mm/rev)	Revolution (min^{-1})	Feed rate (mm/rev)
0.5	8000	0.01	6000	0.01	8000	0.01	10000	0.02
1.0	5000	0.02	4000	0.02	6000	0.02	7000	0.04
2.0	2500	0.05	2300	0.04	4700	0.05	6000	0.08
3.0	1900	0.10	1500	0.07	3200	0.10	5500	0.13
6.0	950	0.18	750	0.10	1600	0.18	3100	0.23
8.0	700	0.20	530	0.13	1200	0.20	2300	0.28
10.0	560	0.22	420	0.15	960	0.22	1900	0.33
12.0	460	0.24	340	0.17	800	0.24	1600	0.38
15.0	360	0.26	270	0.20	630	0.26	1300	0.42
20.0	270	0.28	200	0.23	470	0.28	950	0.45
25.0	210	0.32	160	0.24	380	0.32	750	0.48
30.0	180	0.35	135	0.25	310	0.35	630	0.50

1) Please reduce the cutting conditions when drilling a deep hole.
2) This table only shows standard cutting conditions with water-soluble cutting fluids. Please make corrections or adjustments depending on the application.

Reduction rate of cutting conditions for hole drilling

Drilling depth	Reduction rate of cutting speed	Reduction rate of feed
4D	10%	10%
5D	10%	15%
6D	20%	20%
7D	20%	20%

Drilling depth	Reduction rate of cutting speed	Reduction rate of feed
8D	30%	20%
10D	30%	25%
15D	40%	30%
20D	40%	45%

D : Drill dia.