

## RECOMMENDED CUTTING CONDITIONS

Work Material	Stainless steel				Carbon steel AISI 1049 Alloy steel SCM Cast iron FC Copper, Copper alloy		Structural steel Aluminium alloy	
	Austenitic AISI 304, AISI 316		Martensitic Ferritic AISI 430					
Drill Dia. <b>DC (mm)</b>	Revolution (min <sup>-1</sup> )	Feed rate (mm/rev)	Revolution (min <sup>-1</sup> )	Feed rate (mm/rev)	Revolution (min <sup>-1</sup> )	Feed rate (mm/rev)	Revolution (min <sup>-1</sup> )	Feed rate (mm/rev)
<b>0.5</b>	7600	0.01	8800	0.01	11250	0.01	15000	0.02
<b>1.0</b>	4800	0.02	6300	0.05	10000	0.05	12000	0.05
<b>2.0</b>	2400	0.04	3200	0.06	5500	0.09	6400	0.09
<b>3.0</b>	1600	0.07	2100	0.10	3700	0.13	4300	0.13
<b>4.0</b>	1200	0.09	1600	0.10	2800	0.15	3200	0.15
<b>5.0</b>	950	0.12	1300	0.13	2200	0.18	2600	0.18
<b>6.0</b>	800	0.14	1100	0.15	1800	0.20	2100	0.19
<b>8.0</b>	600	0.18	800	0.18	1400	0.22	1600	0.24
<b>10.0</b>	480	0.22	640	0.21	1100	0.25	1300	0.28
<b>12.0</b>	400	0.24	530	0.25	930	0.30	1100	0.34
<b>13.0</b>	370	0.26	490	0.28	860	0.32	1000	0.36
<b>14.0</b>	340	0.30	450	0.27	730	0.31	930	0.36
<b>15.0</b>	320	0.31	425	0.28	680	0.32	870	0.38
<b>16.0</b>	300	0.32	400	0.30	640	0.34	820	0.42
<b>18.0</b>	270	0.34	350	0.32	570	0.36	725	0.43
<b>20.0</b>	240	0.36	320	0.35	510	0.38	660	0.45

1) Please reduce the revolution and feed rate depending on the drilling situation when the installation of workpiece or machine lacks rigidity.

2) Please use a collet type drill chuck or a milling chuck.

3) Use sufficient cutting fluid.

4) For precipitation-hardened stainless steels (JIS SUS630 and SUS631), MWE and MWS are recommended.

5) When drilling holes greater than 4 x drill diameter hole depths, please use a peck feed.

The above-mentioned cutting condition is standard when using water-soluble cutting fluid.

Please reduce the revolution when using non-water-soluble cutting fluid.