

General Purpose End Mill Recommended Cutting Data - Profile Milling

Length	2 Flute Series		3 Flute Series		4 Flute Series		
Stub	164	166	169		163		165
Standard	121	150	116	145	111	140	151/117 114
Long Length/Reach	123*	183/186			122*	181	184 132*

*Chip thinning may not be possible with 122, 123 and 132 series if radial width of cut exceeds 20%.

For ball nose end mills - If axial depth (ap) is less than the ball diameter, the speed is figured using the effective cutting diameter.

Inch

For diameters 1/4" and below, see Micro Charts starting on page 333.

Workpiece Material Group	ISO	Hardness	Coolant			Profile Milling (ae)					End Mill Diameters					
			● Preferred ○ Possible x Not Possible								5/16	3/8	1/2	5/8	3/4	1
			Max.	Air	MMS	5%	10%	20%	30%	50%	ae > .3D use < 1D ap ae < .2D use < 2D ap					
						vc - SFM Increase speeds by 30% for ALtima® coated tools					← Multiply fz by this Factor based on ae. When finishing, use the standard fz per chart below. Only add chip thinning when roughing or semi-finishing.					
Free Machining & Low Carbon Steels 1006, 1008, 1015, 1018, 1020, 1022, 1025, 1117, 1140, 1141, 11L08, 11L14, 1213, 12L13, 12L14, 1215, 1330	P	up to 28 Rc	●	●	●	1050	700	385	375	350	.0027	.0032	.0045	.0054	.0063	.0090
Medium Carbon & High Carbon Steels, Alloy Steels & Easy to Machine Tool Steels 1030, 1035, 1040, 1045, 1050, 1052, 1055, 1060, 1085, 1095, 1541, 1551, 9255, 2515, 3135, 3415, 4130, 4137, 4140, 4150, 4320, 4340, 4520, 5015, 5115, 5120, 5132, 5140, 5155, 6150, 8620, 9262, 9840, 52100, O1, O2, O6, S2, W1 to W310	P	28 to 38 Rc	●	●	●	630	420	320	250	210	.0027	.0032	.0045	.0054	.0063	.0090
Tool Steels & Die Steels O7, M1, M2, M3, M4, M7, T1, T2, T4, T5, T8, T15, A2, A3, A6, A7, H10, H11, H12, H13, H19, H21, L3, L6, L7, P2, P20, S1, S5, S7, 52100, A 128, D2, D3, D4, D5, D7	P	28 to 44 Rc	●	●	●	525	350	300	275	250	.0027	.0032	.0045	.0054	.0063	.0090
Hardened Steels	H	45-55 Rc	●	○	○	250	240	230	210	200	.0018	.0021	.0030	.0036	.0042	.0060
Hardened Steels		55-65 Rc	●	○	○	200	180	160	150	100	.0013	.0014	.0021	.0024	.0029	.0041
Stainless Steel - Easy to Machine 430F, 301, 303, 410, 416 Annealed, 420F, 430, 430F	M	up to 28 Rc	●	x	○	650	600	550	500	450	.0027	.0032	.0045	.0054	.0063	.0090
Stainless Steel - Moderately Difficult 301, 302, 303 High Tensile, 304, 304L, 305, 420, 15-5PH, 17-4PH, 17-7PH	M	up to 28 Rc	●	x	○	525	400	350	300	250	.0027	.0032	.0045	.0054	.0063	.0090
Stainless Steel - Difficult to Machine 302B, 304B, 309, 310, 316, 316B, 316L, 316Ti, 317, 317L, 321, PH13-8Mo, Nitronics	M	over 28 Rc	●	x	○	525	400	350	300	250	.0027	.0032	.0045	.0054	.0063	.0090

Technical data provided should be considered advisory only as variations may be necessary depending on the particular application.