





CrazyDrill Twicenter 60°

CENTERING WITH INTEGRATED COOLING | CUTTING DATA OVERVIEW

Materials group	Material	Mat. no.	DIN	AISI/ASTM/UNS	V _c [m/min] [SFM]
   <p>Note: In case of external cooling reduce v_c and f of 20%</p>	P Unalloyed carbon steel R _m < 800 N/mm ²	1.0301	C10	AISI 1010	120 394
		1.0401	C15	AISI 1015	
		1.1191	C45E/CK45	AISI 1045	
		1.0044	S275JR	AISI 1020	
		1.0715	11SMn30	AISI 1215	
	Low alloyed steel R _m > 900 N/mm ²	1.5752	15NiCr13	ASTM 3415 / AISI 3310	80 262
		1.7131	16MnCr5	AISI 5115	
		1.3505	100Cr6	AISI 52100	
		1.7225	42CrMo4	AISI 4140	
		1.2842	90MnCrV8	AISI O2	
	High alloyed tool steel R _m < 1200 N/mm ²	1.2379	X153CrMoV12	AISI D2	60 197
		1.2436	X210CrW12	AISI D4/D6	
		1.3343	H56-5-2C	AISI M2 / UNS T11302	
1.3355		H518-0-1	AISI T1 / UNS T12001		
M Stainless steel ferritic martensitic austenitic		1.4016	X6Cr17	AISI 430 / UNS S43000	
	1.4105	X6CrMoS17	AISI 430F	60 197	
	1.4034	X46Cr13	AISI 420C		
	1.4112	X90CrMoV18	AISI 440B	50 164	
	1.4542	X5CrNiCuNb 16-4	AISI 630 / ASTM 17-4 PH		
	1.4545	X5CrNiCuNb 15-5	ASTM 15-5 PH		
	1.4301	X5CrNi 18-10	AISI 304	50 164	
	1.4435	X2CrNiMo 18-14-3	AISI 316L		
1.4441	X2CrNiMo 18-15-3	AISI 316LM			
1.4539	X1NiCrMoCu 25-20-5	AISI 904L			
K Cast iron	0.6020	GG20	ASTM 30	100 328	
	0.6030	GG30	ASTM 40B		
	0.7040	GGG40	ASTM 60-40-18		
	0.7060	GGG60	ASTM 80-60-03		
N Aluminium alloy wrought cast Copper Brass lead free Brass, Bronze R _m < 400 N/mm ² Bronze R _m < 600 N/mm ²	3.2315	AlMgSi1	ASTM 6351	150 492	
	3.4365	AlZnMgCu1.5	ASTM 7075		
	3.2163	GD-AlSi9Cu3	ASTM A380	100 328	
	3.2381	GD-AlSi10Mg	UNS A03590		
	2.004	Cu-OF / CW008A	UNS C10100	100 328	
	2.0065	Cu-ETP / CW004A	UNS C11000		
	2.0321	CuZn37 CW508L	UNS C27400	80 262	
	2.036	CuZn40 CW509L	UNS C28000		
	2.0401	CuZn39Pb3 / CW614N	UNS C38500	100 328	
	2.102	CuSn6	UNS C51900		
2.0966	CuAl10Ni5Fe4	UNS C63000	80 262		
2.096	CuAl9Mn2	UNS C63200			
S₁ Super alloys	2.4856		Inconel 625	10 – 30 33 – 98	
	2.4668		Inconel 718		
	2.4617	NiMo28	Hastelloy B-2		
	2.4665	NiCr22Fe18Mo	Hastelloy X		
S₂ Titanium pure Titanium alloys	3.7035	Gr.2	ASTM B348 / F67	25 82	
	3.7065	Gr.4	ASTM B348 / F68		
S₃ CrCo alloys	3.7165	TiAl6V4	ASTM B348 / F136	25 82	
	9.9367	TiAl6Nb7	ASTM F1295		
H₁ H₂ Hardened steel < 55 HRC Hardened steel ≥ 55 HRC	2.4964	CoCr20W15Ni	Haynes 25	40 – 50 131 – 164	
		CrCoMo28	ASTM F1537		
	Hardened steel < 55 HRC	1.2510	100MnCrMoW4	AISI O1	40 131
	Hardened steel ≥ 55 HRC	1.2379	X153CrMoV12	AISI D2	

RECOMMENDATION FOR USE

● Excellent | ● Good | ○ Acceptable | ⊗ Not recommended



f [mm/rev] | [IPR]

Ød1 0.3 mm .012"	Ød1 0.5 mm .018"	Ød1 1.0 mm .039"	Ød1 1.5 mm .059"	Ød1 2.0 mm .079"	Ød1 3.0 mm .118"	Ød1 4.0 mm .158"	Ød1 6.0 mm .236"
f	f	f	f	f	f	f	f
0.030 .0012	0.050 .0020	0.080 .0031	0.100 .0039	0.120 .0047	0.150 .0059	0.200 .0079	0.250 .0098
0.030 .0012	0.050 .0020	0.080 .0031	0.100 .0039	0.120 .0047	0.150 .0059	0.200 .0079	0.250 .0098
0.020 .0008	0.030 .0012	0.040 .0016	0.060 .0024	0.080 .0031	0.120 .0047	0.180 .0071	0.230 .0091
0.020 .0008	0.030 .0012	0.040 .0016	0.060 .0024	0.080 .0031	0.100 .0039	0.120 .0047	0.150 .0059
0.020 .0008	0.030 .0012	0.040 .0016	0.060 .0024	0.080 .0031	0.120 .0047	0.180 .0071	0.230 .0091
0.020 .0008	0.030 .0012	0.040 .0016	0.060 .0024	0.070 .0028	0.090 .0035	0.110 .0043	0.130 .0051
0.020 .0008	0.030 .0012	0.040 .0016	0.060 .0024	0.070 .0028	0.090 .0035	0.110 .0043	0.130 .0051
0.030 .0012	0.040 .0016	0.050 .0020	0.070 .0028	0.090 .0035	0.110 .0043	0.150 .0059	0.200 .0079
0.040 .0016	0.060 .0024	0.090 .0035	0.110 .0043	0.130 .0051	0.180 .0071	0.230 .0091	0.300 .0118
0.040 .0016	0.060 .0024	0.090 .0035	0.110 .0043	0.130 .0051	0.180 .0071	0.230 .0091	0.300 .0118
0.040 .0016	0.060 .0024	0.090 .0035	0.110 .0043	0.130 .0051	0.180 .0071	0.230 .0091	0.300 .0118
0.040 .0016	0.060 .0024	0.090 .0035	0.110 .0043	0.130 .0051	0.160 .0063	0.180 .0071	0.200 .0079
0.040 .0016	0.060 .0024	0.090 .0035	0.110 .0043	0.130 .0051	0.160 .0063	0.180 .0071	0.200 .0079
0.040 .0016	0.060 .0024	0.090 .0035	0.100 .0039	0.130 .0051	0.160 .0063	0.180 .0071	0.200 .0079
0.015 .0006	0.025 .0010	0.030 .0012	0.040 .0016	0.050 .0020	0.070 .0028	0.090 .0035	0.110 .0043
0.020 .0008	0.030 .0012	0.040 .0016	0.060 .0024	0.070 .0028	0.090 .0035	0.110 .0043	0.130 .0051
0.030 .0012	0.040 .0016	0.070 .0028	0.090 .0035	0.110 .0043	0.140 .0055	0.180 .0071	0.220 .0087
0.020 .0008	0.030 .0012	0.040 .0016	0.060 .0024	0.080 .0031	0.100 .0039	0.110 .0043	0.130 .0051
0.010 .0004	0.020 .0008	0.030 .0012	0.040 .0016	0.050 .0020	0.060 .0024	0.070 .0028	0.080 .0031