

## RECOMMENDED CUTTING CONDITIONS

Work material	Carbon steel, Cast iron, Alloy steel (—30HRC)		Alloy steel, Tool steel, Pre-hardened steel		Austenitic stainless steel, Titanium alloy		Hardened steel (45—55HRC)	
	AISI 1050, AISI No 35 B, AISI P20		AISI H13, AISI W1-10, AISI P21		AISI 304, AISI 306, Ti-6Al-4V		AISI H13	
Dia. DC (mm)	Revolution (min <sup>-1</sup> )	Feed rate (mm/min)	Revolution (min <sup>-1</sup> )	Feed rate (mm/min)	Revolution (min <sup>-1</sup> )	Feed rate (mm/min)	Revolution (min <sup>-1</sup> )	Feed rate (mm/min)
0.1	40000	— (40)	40000	— (40)	40000	— (35)	40000	— (25)
0.2	40000	— (45)	40000	— (45)	40000	— (35)	32000	— (25)
0.3	40000	— (55)	32000	— (45)	27000	— (35)	21000	— (25)
0.4	32000	— (60)	24000	— (45)	20000	— (35)	16000	— (25)
0.5	25000	— (60)	19000	— (45)	16000	— (35)	13000	— (25)
0.6	21000	— (60)	16000	— (45)	13000	— (35)	11000	— (25)
0.7	18000	— (60)	14000	— (45)	11000	— (35)	9100	— (25)
0.8	16000	— (60)	12000	— (45)	9900	— (35)	8000	— (25)
0.9	14000	— (60)	11000	— (45)	8800	— (35)	7100	— (25)
1	13000	60 (60)	9500	45 (45)	8000	35 (35)	6400	25 (25)
1.5	8500	60 (60)	6400	45 (45)	5300	35 (35)	4200	25 (25)
2	6400	60 (60)	4800	45 (45)	4000	35 (35)	3200	25 (25)
2.5	5100	60 (60)	3800	45 (45)	3200	40 (40)	2500	25 (25)
3	4200	65 (60)	3400	55 (45)	2600	40 (40)	2100	25 (25)
4	3400	80 (60)	2700	65 (45)	2100 (1600)	50 (30)	1700	35 (25)
5	2900	100 (60)	2300	80 (45)	1800 (1350)	60 (30)	1500	40 (25)
6	2500	120 (60)	2000	100 (50)	1500 (1100)	75 (30)	1300	50 (25)
8	1900	130 (60)	1500	100 (50)	1200 (900)	80 (30)	1000	50 (25)
10	1600	130 (60)	1300	100 (50)	950 (710)	75 (30)	800	50 (25)
12	1300	120 (60)	1100	100 (50)	800 (600)	75 (30)	670	50 (25)
Depth of cut	<p> <math>\leq 0.05DC</math> (MAX. 0.5mm)  <math>\leq 2.5DC</math>                      (DC <math>\geq \phi 1</math>)                 </p>				<p> <math>\leq 0.02DC</math>  <math>\leq 2DC</math>                      (DC <math>\geq \phi 1</math>)                 </p>			
	<p> <math>\leq 0.02DC</math> (DC <math>&lt; \phi 0.5</math>)  <math>\leq 0.05DC</math> (<math>\phi 0.5 \leq DC &lt; \phi 1</math>)  <math>\leq 0.1DC</math> (<math>\phi 1 \leq DC &lt; \phi 2</math>)  <math>\leq 0.2DC</math> (DC <math>\geq \phi 2</math>)                 </p>				<p> <math>\leq 0.02DC</math> (DC <math>&lt; \phi 0.5</math>)  <math>\leq 0.05DC</math> (DC <math>\leq \phi 0.5</math>)                 </p>			

( ) : Indicates standard revolution and feed rate for slotting.

DC: Dia.

- 1) When cutting austenitic stainless steels, the use of water-soluble cutting fluid is effective.
- 2) If the depth of cut is shallow, the revolution and feed rate can be increased.
- 3) When drilling, please set the feed rate at 1/3 or below the values above.
- 4) If the rigidity of the machine or the work materials installation is very low, or chattering and noise are generated, reduce the revolution and feed rate proportionately.