

MSTAR END MILLS

CARBIDE

MS2XL6

End mill, Short cut length, 2 flute, 6mm shank

RECOMMENDED CUTTING CONDITIONS

Work material		Carbon steel, Cast iron, Alloy steel (—30HRC) AISI 1050, AISI No 35 B, AISI P20			Alloy steel, Tool steel, Pre-hardened steel AISI H13, AISI W1-10, AISI P21		
Dia. DC (mm)	Neck length LU (mm)	Revolution (min ⁻¹)	Feed rate (mm/min)	Depth of cut ap (mm)	Revolution (min ⁻¹)	Feed rate (mm/min)	Depth of cut ap (mm)
0.3	—	40000	500—1000	0.01	30000	300—800	0.01
	1.5			0.007			0.007
0.4	1	40000	500—1000	0.015	30000	300—800	0.015
	2			0.01			0.01
0.5	1.3	40000	500—1000	0.02	30000	300—800	0.02
	2.5			0.013			0.013
0.6	1.5	33000	500—1000	0.03	25000	300—800	0.03
	3			0.018			0.018
0.7	1.8	29000	500—1000	0.04	22000	300—800	0.04
	3.5			0.025			0.025
0.8	2	25000	500—1000	0.06	20000	300—800	0.06
	4			0.03			0.03
0.9	2.3	22000	500—1000	0.08	18000	300—800	0.08
	4.5			0.05			0.05
1	2.5	20000	500—1000	0.1	16000	300—800	0.1
	5			0.07			0.07
1.1	2.8	18000	500—1000	0.12	14000	300—800	0.12
	5.5			0.08			0.08
1.2	3	16000	500—1000	0.12	13000	300—800	0.12
	6			0.08			0.08
1.3	3.3	15000	500—1000	0.12	12000	300—800	0.12
	6.5			0.08			0.08
1.4	3.5	14000	500—1000	0.12	11000	300—800	0.12
	7			0.08			0.08
1.5	3.8	13000	500—1000	0.15	10000	300—800	0.15
	7.5			0.1			0.1
1.6	4	12000	500—1000	0.15	10000	300—800	0.15
	8			0.1			0.1
1.7	4.3	12000	500—1000	0.17	9500	300—800	0.17
	8.5			0.12			0.12
1.8	4.5	11000	500—1000	0.17	9000	300—800	0.17
	9			0.12			0.12
1.9	4.8	10000	500—1000	0.17	9000	300—800	0.17
	9.5			0.12			0.12
2	5	10000	500—1000	0.2	9000	300—800	0.2
	10			0.15			0.15
2.1	5.3	9800	500—1000	0.2	9000	300—800	0.2
	10.5			0.15			0.15
2.2	5.5	9600	500—1000	0.2	9000	300—800	0.2
	11			0.15			0.15
2.3	5.8	9400	500—1000	0.2	8800	300—800	0.2
	11.5			0.15			0.15
2.4	6	9200	500—1000	0.25	8700	300—800	0.25
	12			0.2			0.2
2.5	6.3	9000	500—1000	0.25	8500	300—800	0.25
	12.5			0.2			0.2

ap:Depth of Cut in the Axial Direction

- 1) If the depth of cut is shallow, the revolution and feed rate can be increased.
- 2) Cutting condition may be considerably different due to the overhang (milling depth), depth of cut, and machine tools. Please see the above table as a standard.