

# MSTAR END MILLS

CARBIDE

## MSPES

End mill, 2 flute, For small automatic lathes

### RECOMMENDED CUTTING CONDITIONS

Work material	Carbon steel, Cast iron, Alloy steel (—30HRC)		Alloy steel, Tool steel, Pre-hardened steel		Austenitic stainless steel, Titanium alloy		Hardened steel (45—55HRC)	
	AISI 1050, AISI No 35 B, AISI P20		AISI H13, AISI W1-10, AISI P21		AISI 304, AISI 306, Ti-6Al-4V		AISI H13	
Dia. DC (mm)	Revolution (min <sup>-1</sup> )	Feed rate (mm/min)	Revolution (min <sup>-1</sup> )	Feed rate (mm/min)	Revolution (min <sup>-1</sup> )	Feed rate (mm/min)	Revolution (min <sup>-1</sup> )	Feed rate (mm/min)
<b>3</b>	10000	600	7000	400	6000	300	5000	120
<b>4</b>	7500	600	5200	400	4500	300	4000	120
<b>5</b>	6000	600	4200	400	3600	300	3200	120
<b>6</b>	5000	600	3500	400	3000	300	2700	120
<b>7</b>	4500	560	3000	360	2700	280	2300	110
<b>8</b>	4000	520	2800	350	2400	260	2000	110
<b>10</b>	3200	450	2200	300	1900	230	1600	100
<b>12</b>	2700	410	1900	270	1600	210	1300	100

  

Depth of cut	Carbon steel, Cast iron, Alloy steel (—30HRC)		Alloy steel, Tool steel, Pre-hardened steel		Austenitic stainless steel, Titanium alloy		Hardened steel (45—55HRC)	
	AISI 1050, AISI No 35 B, AISI P20		AISI H13, AISI W1-10, AISI P21		AISI 304, AISI 306, Ti-6Al-4V		AISI H13	

DC:Dia.

- 1) When cutting austenitic stainless steels, the use of water-soluble cutting fluid is effective.
- 2) If the depth of cut is shallow, the revolution and feed rate can be increased.
- 3) When drilling, please set the feed rate at 1/3 or below the values above.
- 4) If the rigidity of the machine or the work materials installation is very low, or chattering and noise are generated, reduce the revolution and feed rate proportionately.

SOLID END MILLS