

IMPACT MIRACLE END MILLS

CARBIDE

VFMFPR

Roughing end mill, Medium cut length, 4 flute

RECOMMENDED CUTTING CONDITIONS

Side milling

Work material	Carbon steel, Cast iron, Alloy steel (—30HRC)		Alloy steel, Tool steel, Pre-hardened steel		Austenitic stainless steel, Titanium alloy		Hardened steel (45—55HRC)		Heat resistant alloys	
	AISI 1050, AISI No 35 B, AISI P20		AISI H13, AISI W1-10, AISI P21		AISI 304, AISI 306, Ti-6Al-4V		AISI H13		Inconel718	
Dia. DC (mm)	Revolution (min ⁻¹)	Feed rate (mm/min)	Revolution (min ⁻¹)	Feed rate (mm/min)	Revolution (min ⁻¹)	Feed rate (mm/min)	Revolution (min ⁻¹)	Feed rate (mm/min)	Revolution (min ⁻¹)	Feed rate (mm/min)
5	3800	360	3200	290	2500	150	2500	150	1900	50
6	3200	360	2700	290	2100	160	2100	160	1600	60
8	2400	450	2000	360	1600	160	1600	160	1200	70
10	1900	450	1600	360	1300	180	1300	180	1000	75
12	1600	400	1300	320	1100	180	1100	180	800	80
16	1200	360	1000	290	800	160	800	160	600	80
20	1000	340	800	270	600	150	600	150	500	80

Depth of cut		
	DC: Dia.	

- 1) When cutting austenitic stainless steels, the use of water-soluble cutting fluid is effective.
- 2) If the depth of cut is shallow, the revolution and feed rate can be increased.
- 3) If the rigidity of the machine or the work materials installation is very low, or chattering and noise are generated, reduce the revolution and feed rate proportionately.

SOLID END MILLS