




RECOMMENDED CUTTING CONDITIONS

Side milling




Work material	Carbon steel, Cast iron, Alloy steel (—30HRC)		Alloy steel, Tool steel, Pre-hardened steel		Austenitic stainless steel, Titanium alloy		Hardened steel (45—55HRC)		Heat resistant alloys	
	AISI 1050, AISI No 35 B, AISI P20		AISI H13, AISI W1-10, AISI P21		AISI 304, AISI 306, Ti-6Al-4V		AISI H13		Inconel718	
Dia. DC (mm)	Revolution (min ⁻¹)	Feed rate (mm/min)	Revolution (min ⁻¹)	Feed rate (mm/min)	Revolution (min ⁻¹)	Feed rate (mm/min)	Revolution (min ⁻¹)	Feed rate (mm/min)	Revolution (min ⁻¹)	Feed rate (mm/min)
2	15000	550	10000	340	10000	320	6400	160	4800	100
3	11000	800	7400	500	7400	480	4800	250	4000	170
4	8000	900	5600	540	5600	520	3600	270	3200	240
5	6400	1000	4500	600	4500	580	2900	300	2600	240
6	5900	1100	3700	640	3700	600	2400	320	2100	230
8	4400	1100	2800	660	2800	600	1800	330	1600	220
10	3500	1000	2300	640	2300	560	1400	320	1300	200
12	2900	1000	1900	640	1900	530	1200	320	1100	170
16	2200	800	1400	500	1400	450	900	250	800	130
18	2000	800	1250	480	1250	450	800	240	710	110
20	1800	750	1100	460	1100	440	720	230	650	100

Depth of cut	Carbon steel, Cast iron, Alloy steel (—30HRC)		Alloy steel, Tool steel, Pre-hardened steel		Austenitic stainless steel, Titanium alloy		Hardened steel (45—55HRC)		Heat resistant alloys	
	AISI 1050, AISI No 35 B, AISI P20		AISI H13, AISI W1-10, AISI P21		AISI 304, AISI 306, Ti-6Al-4V		AISI H13		Inconel718	
										

DC:Dia.

Slotting

Work material	Carbon steel, Cast iron, Alloy steel (—30HRC)		Alloy steel, Tool steel, Pre-hardened steel		Austenitic stainless steel, Titanium alloy		Hardened steel (45—55HRC)		Heat resistant alloys	
	AISI 1050, AISI No 35 B, AISI P20		AISI H13, AISI W1-10, AISI P21		AISI 304, AISI 306, Ti-6Al-4V		AISI H13		Inconel718	
Dia. DC (mm)	Revolution (min ⁻¹)	Feed rate (mm/min)	Revolution (min ⁻¹)	Feed rate (mm/min)	Revolution (min ⁻¹)	Feed rate (mm/min)	Revolution (min ⁻¹)	Feed rate (mm/min)	Revolution (min ⁻¹)	Feed rate (mm/min)
2	12000	400	7000	200	7000	100	4200	80	2300	40
3	9000	600	5300	300	5300	150	3200	130	1900	70
4	7200	720	4000	360	4000	180	2400	140	1400	95
5	5800	720	3200	360	3200	180	1900	150	1100	95
6	5000	800	2700	400	2700	200	1600	160	950	95
8	3700	800	2000	400	2000	200	1200	170	720	90
10	3000	720	1600	360	1600	180	960	160	570	80
12	2500	600	1300	290	1300	150	800	140	480	70
16	2000	480	1000	230	1000	120	600	110	360	50
18	1800	460	900	210	900	110	550	110	320	45
20	1600	430	800	200	800	100	480	100	290	40

Depth of cut	Carbon steel, Cast iron, Alloy steel (—30HRC)		Alloy steel, Tool steel, Pre-hardened steel		Austenitic stainless steel, Titanium alloy		Hardened steel (45—55HRC)		Heat resistant alloys	
	AISI 1050, AISI No 35 B, AISI P20		AISI H13, AISI W1-10, AISI P21		AISI 304, AISI 306, Ti-6Al-4V		AISI H13		Inconel718	
										

DC:Dia.

- 1) When cutting austenitic stainless steels, the use of water-soluble cutting fluid is effective.
- 2) If the depth of cut is shallow, the revolution and feed rate can be increased.
- 3) If the rigidity of the machine or the work materials installation is very low, or chattering and noise are generated, reduce the revolution and feed rate proportionately.