

■ Series 4Q03 4Q05 4Q43 • Victory Grades



Material Group							Recommended feed per tooth (IPT = inch/th) for side milling (A). For slotting (B), reduce IPT by 20%.										
	Side Milling (A) and Slotting (B)		WP15PE			D1 – Diameter											
	A		B		Cutting Speed – vc SFM			frac.									
	ap	ae	ap	min		max	dec.	3/16	1/4	5/16	3/8	1/2	5/8	3/4	1		
P	0	1 x D	0.5 x D	0.75 x D	490	–	660	IPT	.0014	.0018	.0023	.0027	.0034	.0040	.0044	.0049	
	1	1 x D	0.5 x D	0.75 x D	490	–	660	IPT	.0014	.0018	.0023	.0027	.0034	.0040	.0044	.0049	
	2	1 x D	0.5 x D	0.75 x D	460	–	620	IPT	.0014	.0018	.0023	.0027	.0034	.0040	.0044	.0049	
	3	1 x D	0.5 x D	0.75 x D	390	–	520	IPT	.0011	.0015	.0020	.0023	.0029	.0034	.0039	.0045	
	4	1 x D	0.4 x D	0.5 x D	300	–	490	IPT	.0010	.0014	.0018	.0020	.0026	.0030	.0034	.0039	
	5	1 x D	0.5 x D	0.75 x D	200	–	330	IPT	.0009	.0012	.0016	.0018	.0023	.0027	.0031	.0036	
M	1	1 x D	0.5 x D	0.75 x D	300	–	380	IPT	.0011	.0015	.0020	.0023	.0029	.0034	.0039	.0045	
	2	1 x D	0.4 x D	0.75 x D	200	–	260	IPT	.0009	.0012	.0016	.0018	.0023	.0027	.0031	.0036	
	3	1 x D	0.4 x D	0.75 x D	200	–	230	IPT	.0008	.0010	.0013	.0015	.0019	.0022	.0025	.0028	
K	1	1 x D	0.5 x D	0.75 x D	390	–	490	IPT	.0014	.0018	.0023	.0027	.0034	.0040	.0044	.0049	
	2	1 x D	0.5 x D	0.75 x D	360	–	460	IPT	.0011	.0015	.0020	.0023	.0029	.0034	.0039	.0045	
	3	1 x D	0.4 x D	0.75 x D	360	–	430	IPT	.0009	.0012	.0016	.0018	.0023	.0027	.0031	.0036	
S	1	1 x D	0.3 x D	0.4 x D	160	–	300	IPT	.0011	.0015	.0020	.0023	.0029	.0034	.0039	.0045	
	2	1 x D	0.3 x D	0.3 x D	80	–	130	IPT	.0006	.0008	.0010	.0012	.0015	.0018	.0021	.0024	
	3	1 x D	0.4 x D	0.75 x D	200	–	260	IPT	.0009	.0012	.0016	.0018	.0023	.0027	.0031	.0036	
	4	1 x D	0.4 x D	0.75 x D	160	–	200	IPT	.0008	.0011	.0014	.0017	.0021	.0025	.0028	.0033	
H	1	1 x D	0.2 x D	0.3 x D	260	–	460	IPT	.0010	.0014	.0018	.0020	.0026	.0030	.0034	.0039	

NOTE: Lower value of cutting speed is used for high stock removal applications or for higher hardness (machinability) within group.
 Higher value of cutting speed is used for finishing applications or for lower hardness (machinability) within group.
 Above parameters are based on ideal conditions. For smaller taper machining centers, please adjust parameters accordingly on >1/2" diameter.

High-Performance Solid Carbide End Mills