

■ Series 5VNC • VariMill II • With Neck • Victory Grades



Material Group							Recommended feed per tooth (IPT = inch/th) for side milling (A). For slotting (B), reduce IPT by 20%.								
	Side Milling (A) and Slotting (B)		WP15PE				D1 – Diameter								
	A		B		Cutting Speed – vc SFM		frac.	1/4	5/16	3/8	1/2	5/8	3/4	1	
	ap	ae	ap	min	max	dec.	.2500	.3125	.3750	.5000	.6250	.7500	1.0000		
P	5	1.5 x D	0.5 x D	1 x D	200	–	330	IPT	.0012	.0016	.0018	.0023	.0027	.0031	.0036
	6	1.5 x D	0.5 x D	0.75 x D	160	–	250	IPT	.0010	.0013	.0015	.0019	.0022	.0025	.0028
M	1	1.5 x D	0.5 x D	1 x D	300	–	380	IPT	.0015	.0020	.0023	.0029	.0034	.0039	.0045
	2	1.5 x D	0.5 x D	1 x D	200	–	260	IPT	.0012	.0016	.0018	.0023	.0027	.0031	.0036
K	3	1.5 x D	0.5 x D	1 x D	200	–	230	IPT	.0010	.0013	.0015	.0019	.0022	.0025	.0028
	1	1.5 x D	0.5 x D	1 x D	390	–	490	IPT	.0018	.0023	.0027	.0034	.0040	.0044	.0049
	2	1.5 x D	0.5 x D	1 x D	360	–	460	IPT	.0015	.0020	.0023	.0029	.0034	.0039	.0045
S	3	1.5 x D	0.5 x D	1 x D	360	–	430	IPT	.0012	.0016	.0018	.0023	.0027	.0031	.0036
	1	1.5 x D	0.3 x D	0.3 x D	160	–	300	IPT	.0015	.0020	.0023	.0029	.0034	.0039	.0045
	2	1.5 x D	0.3 x D	0.3 x D	80	–	130	IPT	.0008	.0010	.0012	.0015	.0018	.0021	.0024
	3	1.5 x D	0.3 x D	0.3 x D	200	–	260	IPT	.0012	.0016	.0018	.0023	.0027	.0031	.0036
H	4	1.5 x D	0.5 x D	1 x D	160	–	200	IPT	.0011	.0014	.0017	.0021	.0025	.0028	.0033
	1	1.5 x D	0.5 x D	0.75 x D	260	–	460	IPT	.0014	.0018	.0020	.0026	.0030	.0034	.0039
H	2	1.5 x D	0.2 x D	0.5 x D	230	–	390	IPT	.0010	.0013	.0015	.0019	.0022	.0025	.0028

NOTE: Lower value of cutting speed is used for high stock removal applications or for higher hardness (machinability) within group.
 Higher value of cutting speed is used for finishing applications or for lower hardness (machinability) within group.
 Above parameters are based on ideal conditions. For smaller taper machining centers, please adjust parameters accordingly on >1/2" diameter.

High-Performance Solid Carbide End Mills