



# TECHNICAL DATA | WINNER |

## WR504 Series

Work Material	Alloy Steels, Carbon Steels (SCM, SNCM, S45C)		Prehardened Steels (NAK, CENA, KP4)		Hardened Steels (SKD, SKT, STAVAX)	
Hardness	≤ 35 HRc		35 ~ 45 HRc		45 ~ 55 HRc	
Strength	≤ 1100N / mm <sup>2</sup>		1100~1500N / mm <sup>2</sup>		1500~2000N / mm <sup>2</sup>	
Cutting Diameter (metric)	RPM	FEED	RPM	FEED	RPM	FEED
3.0	4,410	115	3,570	100	2,200	55
4.0	3,570	140	2,840	115	1,790	60
5.0	3,050	180	2,420	140	1,580	70
6.0	2,630	215	2,100	180	1,370	85
8.0	2,000	230	1,580	180	1,050	85
10.0	1,680	230	1,370	180	840	85
12.0	1,370	180	1,160	160	700	70
16.0	1,160	160	890	125	560	60
20.0	840	115	680	90	420	45

RPM = rev. / min.  
FEED = mm / min.



## WR514 Series

Work Material	Alloy Steels, Carbon Steels (SCM, SNCM, S45C)		Prehardened Steels (NAK, CENA, KP4)		Hardened Steels (SKD, SKT, STAVAX)	
Hardness	≤ 35 HRc		35 ~ 45 HRc		45 ~ 55 HRc	
Strength	≤ 1100N / mm <sup>2</sup>		1100~1500N / mm <sup>2</sup>		1500~2000N / mm <sup>2</sup>	
Cutting Diameter (metric)	RPM	FEED	RPM	FEED	RPM	FEED
0.2	50,000	170	34,500	75	21,150	45
0.3	50,000	200	32,000	85	20,000	50
0.4	50,000	200	32,000	85	20,000	50
0.5	43,000	220	28,000	95	17,100	60
0.6	36,400	250	24,000	110	14,500	65
0.8	36,400	250	24,000	110	14,500	65
1.0	33,100	280	21,600	120	13,200	70
1.5	26,400	300	16,200	130	10,200	70
2.0	21,600	310	13,800	140	8,640	80
2.5	18,000	320	11,400	150	7,320	80
3.0	15,900	330	10,300	160	6,300	80
4.0	12,800	400	8,200	200	5,150	95
5.0	11,000	500	7,000	240	4,560	120
6.0	9,500	600	6,000	300	3,930	140
8.0	7,200	640	4,550	300	3,020	140
10.0	6,000	640	4,000	300	2,420	140
12.0	5,000	500	3,340	270	2,000	120
16.0	3,720	450	2,520	210	1,540	95
20.0	3,000	330	1,950	140	1,200	70

RPM = rev. / min.  
FEED = mm / min.

