

ZS104, ZS204 series

Work Material	Hardened Steels									
	40 ~ 50 HRc		50 ~ 55 HRc		55 ~ 60 HRc		60 ~ 65 HRc		65 ~ 70 HRc	
Hardness										
Cutting Diameter(metric)	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
4	17,200	1,690	11,440	1,140	9,360	700	7,280	430	6,170	310
6	13,450	1,820	8,970	1,230	6,890	720	5,460	450	4,810	330
8	9,100	1,750	6,760	1,170	5,200	670	4,160	420	3,640	310
10	8,000	1,630	5,330	1,090	4,160	620	3,320	400	2,860	280
12	6,830	1,630	4,550	1,010	3,450	580	2,730	370	2,420	260

RPM = rev. / min.
FEED = mm / min.

